



**MRO COLD GALV PRIMER
 #16-1445**

A cold galvanizing primer that contains 93% Type I inorganic zinc in the dried paint film. Resists oxidation, and the galvanizing protection continues even if scratched. Can be topcoated for maximum durability.

Suggested Uses:

- Touch up galvanized metal
- Zinc protection for iron
- Galvanize metal structures

Use on projects that require 90% minimum zinc content

Packaging:

UPC Code	043281006828
Cans per case	6
Shipping weight per case	7.5 lbs.
Container	16 fluid ounce can
Label weight	15 ounces (425 grams)
Shipping Classification	limited quantity, UN 1950
Hazard Class	2.1

Properties:

Coverage	Up to 15 square feet
Cleanup	Paint or lacquer thinner
Flash point	-4 F
Specific Gravity	0.87
Solids Content	52%
% zinc in dried paint film	93.5%
MIR value	1.18, cannot exceed 1.25
HAPs content	17%
Storage Temperature	40-100F
Application Temperature	50-90F
Durability	Very Good
Abrasion Resistance	Very Good
Heat Resistance	350F
Resin System	Modified Epoxy
Shelf life	Guaranteed for 2 years

Dry Time*:

To touch	5 minutes
To topcoat	20 minutes

*At 72F, 50% humidity, 1.5 mil thickness

Curing/Recoat time is extended with multiple coats and excessively thick coats

Gloss*: Flat, <15

*as measured on a 60 degree gloss meter

Meets or exceeds the following performance requirements:

- ASTM A780
- MIL-P-26915D
- MIL-P-46105
- DOD-P-21035B
- SSPC-Paint 20

12-11-2021

Seymour of Sycamore | 917 Crosby Avenue | Sycamore IL 60178

Phone | 815.895.9101 • 800.435.4482

Fax | 815.895.8475 • 800.343.4258