



MasterFormat: 03 39 23

AUGUST 2025  
(Supersedes March 2025)

## CRISTALLUM

### Premium, Clear, Water-Based Concrete Curing Compound

#### DESCRIPTION

CRISTALLUM is a clear, water-based, dissipating concrete curing compound formulated for use on interior, exterior, vertical, and horizontal concrete surfaces. Once applied, CRISTALLUM forms a premium-grade membrane that retains an optimum amount of water in freshly placed concrete for proper hydration of the concrete. CRISTALLUM fills a critical performance gap in curing compounds for high-end concrete applications where visual appearance during the curing period is a priority.

#### USES

CRISTALLUM can be used on both interior and exterior, vertical and horizontal applications where aesthetic is of a prime importance during the dissipation process. Paint, resilient tile, or resilient flooring may be applied on concrete cured with CRISTALLUM, once the product has dissipated and/or has been properly removed. Because of the wide variety of coatings, paints, adhesives, and toppings available, contact the manufacturer of the flooring system or subsequent coating or topping for application approval over concrete cured with resin-based curing compounds. A small test application is always recommended.

#### FEATURES/BENEFITS

- When properly applied, CRISTALLUM produces a premium-grade film, which optimizes water retention.
- CRISTALLUM dries to a clear film.
- Ideal for use where aesthetic is of prime importance during the curing period.
- Furnished as a ready-to-use, true water-based compound.
- Produces hard, dense concrete ... minimizes hair checking, dusting, and other defects.
- Offers a compressive strength significantly greater than improperly cured or uncured concrete.
- Increases tensile strength for greater resistance to cracking and surface crazing.
- Improves resistance to abrasion and the corrosive actions of salts and chemicals
- Minimizes excessive shrinkage

- Can be applied quickly and easily with conventional commercial spray equipment.
- VOC-compliant.

#### PACKAGING

5 Gallon (18.93 L) Pails  
55 Gallon (208.20 L) Drums  
275 Gallon (1040.99 L) Totes

#### COVERAGE

Approximately 200 ft.<sup>2</sup>/gal. (4.91 m<sup>2</sup>/L). Coverage is approximate and may vary depending on surface finish/texture, concrete condition, climatic conditions, etc. Always apply to a test area first to determine actual coverage rate before full-scale application.

#### SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 40° - 90° F (4° - 32° C), optimum performance and best use is obtained within one year of date of manufacture.

#### SPECIFICATIONS/STANDARDS

- AASHTO M 148, Type 1, Classes A & B (Type 1-D also available)
- ASTM C309, Type 1, Classes A & B (Type 1-D also available)
- Complies with all current federal, state, and local maximum allowable VOC requirements, including National EPA VOC Emission Standard for Architectural Coatings, CARB, LADCO, OTC Phase I and II, and SCAQMD.

#### APPLICATION

**Mixing** ... For optimum performance, gentle mixing or agitation is recommended. CAUTION: TO AVOID FOAMING, DO NOT MIX EXCESSIVELY. DO NOT THIN.

*CONTINUED ON REVERSE SIDE ...*

#### W. R. MEADOWS, INC.

P.O. Box 338 • Hampshire, IL 60140-0338  
Phone: 847/214-2100 • Fax: 847/683-4544  
1-800-342-5976  
www.wrmeadows.com • info@wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA  
FORT WORTH, TX / BENICIA, CA / POMONA, CA  
GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB

**Application Method ...** Application equipment must be clean and free of all previously used materials. Apply in a uniform film to horizontal surfaces as soon as the surface water disappears and the surface will not be marred by walking workmen. On vertical surfaces, apply promptly after the forms are removed. CRISTALLUM may be applied with a typical commercial hand or power sprayer, such as a Chapin 1949. Use a spray nozzle that produces a flow of 0.5 GPM (1.9 LPM) under 40 psi (.276 MPa) of pressure. An even spray pattern/application is essential to the aesthetic and final appearance of the concrete. Be mindful of clogged or partially clogged spray tips that spray CRISTALLUM in an uneven and non-uniform pattern. Do not allow the spray nozzle to drip on fresh concrete. Drips and uneven spray patterns apply higher concentrations of the film, which may cause the cement to hydrate at different rates. Removal of the film will not change the spray patterns mirrored in the concrete surface from the cement hydrating at different rates.

**Drying Time...** Typically dries in 1 - 2 hours, depending on jobsite conditions (temperature, % relative humidity, wind, etc.). Restrict foot traffic for at least four hours. Twelve hours is preferable.

**Cleanup...** Prior to drying, cleanup can be accomplished with soap and water. Once dried, use mineral spirits or other suitable petroleum solvent.

## LIMITATIONS/PRECAUTIONS

KEEP FROM FREEZING. Do not apply if air and/or concrete temperature is less than 40° F (4° C). Improper or over-application may increase the amount of time necessary for the film to dissipate from the surface. DO NOT MIX OR DILUTE WITH ANY OTHER PRODUCTS OR LIQUIDS. Residual membrane must be thoroughly removed prior to painting, topping, or any subsequent treatment. Do not apply paint, resilient flooring, or any other subsequent coatings or toppings without first checking the specifications and securing approval from the manufacturer of the product being applied over concrete cured with CRISTALLUM. A small test application is always recommended, prior to full-scale application. The CRISTALLUM membrane may take longer to dissipate if overapplied or has had limited exposure to UV light and environmental conditions, etc.

## HEALTH AND SAFETY

Direct contact may result in mild irritation. Read and follow all application, precaution, label, and health and safety information prior to use. Refer to Safety Data Sheet for complete health and safety information.



### LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

### Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.

© W. R. MEADOWS 2025