



MasterFormat:
07 92 13
32 13 73

JUNE 2026
(Supersedes June 2025)

POURTHANE® SL

Self-Leveling Joint Sealant

DESCRIPTION

POURTHANE SL is an elastomeric, one-component, self-leveling, non-bubbling, premium-grade polyurethane sealant specifically developed to be used as a multi-purpose horizontal joint sealant. The product is a moisture cure sealant with excellent adhesive properties and resistance to aging and weathering.

USES

POURTHANE SL is used to seal horizontal joints in concrete, such as sidewalks, balconies, pavement, terraces, warehouses, factories, civil structures, plazas, and runways. POURTHANE SL may also be used as a pitch pan sealant.

FEATURES/BENEFITS

- One-component, no mixing.
- Self-leveling.
- Non-bubbling formula can be applied in green or damp concrete.
- Movement capacity of +/-25%.
- Accelerated curing.
- Highly resistant to fuels, including jet fuel.
- Resistant to incidental exposure to ethanol.
- Permanently elastic.
- High durability.
- Resists aging and weathering.
- Excellent adhesion.
- Convenient, easy-to-use packaging.
- Low VOC content.

PACKAGING

29 Oz. (825 mL) Cartridges (12/Cartron)
5 Gal. (18.93 L) Pails
55 Gal. (208.20 L) Drums

AVAILABLE COLORS

Limestone, Gray, Desert Tan

COVERAGE

This chart shows the approximate number of lineal feet that can be sealed per gallon. One gallon is approximately four cartridges.

Joint Depth	Joint Width						
	1/4" (6.4 mm)	3/8" (9.5 mm)	1/2" (12.7 mm)	5/8" (15.9 mm)	3/4" (19.1 mm)	7/8" (22.2 mm)	1" (25.4 mm)
1/4" (6.4 mm)	308	205	154	122			
3/8" (9.5 mm)				82	68	58	51
1/2" (12.7 mm)					51	44	38

When estimating, figure 5 cartridges/gal. (2 cartridges/1.5 L).
Cubic inches/gal. – 231 (1000 cm³)
Cubic inches/cartridge – 50 (825 cm³)

For triangular cross-section joints:

1/4" (6.35 mm) each side – 616 linear ft./gal. (49.6 m/L)
1/2" (12.7 mm) each side – 154 linear ft./gal. (12.4 m/L)
3/4" (19.1 mm) each side – 68 linear ft./gal. (5.5 m/L)

SHELF LIFE

When stored indoors and in original, unopened containers at temperatures between 40° - 95° F (4° - 35° C), shelf life is one year from date of manufacture, except for pails and drums, which have a shelf life of six months.

SPECIFICATIONS/STANDARDS

- ASTM C920-11, Type S, Grade P, Class 25, Use T₁, T₂, NT, M, G, A, I, O.
- Federal Specification TT-S-00230C, Type 1, Class A
- Approval/Standards Conform to 1S0 11600 F 25 HM
- USDA compliant for use in areas that handle meat and poultry

CONTINUED ON REVERSE SIDE ...

W. R. MEADOWS, INC.

P.O. Box 338 • Hampshire, IL 60140-0338
Phone: 847/214-2100 • Fax: 847/683-4544
1-800-342-5976
www.wrmeadows.com • info@wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA
FORT WORTH, TX / BENICIA, CA / POMONA, CA
GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB

TECHNICAL DATA

Property	Typical Value	Test Method
Tensile strength, psi (MPa)	180 (1.23)	ASTM D412
Elongation	785%	ASTM D412
Tear Strength, pli (kN/m)	33 lb./in. (5.8 kN/m)	ASTM D624
Shore A Hardness	30±5	ASTM C661
Movement Capability	±25	ASTM C719
Skin Time 50% RH, 74° F (23° C)	60 - 120 minutes	
Weathering Resistance	Excellent	ASTM C793
Stain and Color Change	Pass	ASTM C510
Application Temperature	41° - 104° F (5° - 40° C)	
Service Range	-40° to 180° F (-40° to 82.2° C)	
Rheological Properties	Pass	ASTM C639
Peel on Aluminum-Dry	25 c.f.	ASTM C794
Peel on Glass-Dry	26 c.f.	ASTM C794
Peel on Concrete Mortar-Dry	24 c.f.	ASTM C794
Paint Compatibility	Water-Based: Compatible	
	Solvent-Based: Check Compatibility	
VOC Content	47 g/L	

APPLICATION

Surface Preparation ... Clean all surfaces. Joint walls must be sound, clean, dry, frost-free, and free of all oil and grease. Curing compound residues and any other foreign matter must be thoroughly removed. Install bond breaker tape or KOOL-ROD™ from W. R. MEADOWS to prevent bond at base of joint. When applying to green concrete, wait 24 hours after forms have been removed. Concrete can be damp during application, but do not apply when standing water is in or near joints.

Priming ... Priming is not usually necessary. Substrates only require priming if testing indicates a need or where sealant will be subjected to water immersion after cure. If priming is required, use REZI-WELD™ LV from W. R. MEADOWS.

Application Method ... Condition material to 65° - 75° F (18.3° - 23.9° C) before using. Sealant should be installed when joint is at mid-range of anticipated movement. Gun sealant into joint opening in one direction and allow sealant to flow and level out as necessary. Tool as required; minimum tooling is necessary. Joint dimensions should allow for 1/4" (6.35 mm) minimum and 1/2" (12.7 mm) maximum thickness for sealant. Proper design is 2:1 width-to-depth ratio. Always use bond breaker tape or KOOL-ROD from W. R. MEADOWS for support on horizontal joints

Drying Time ... Typical skin time is 60 - 120 minutes. A reasonable elapsed time for full cure of POURTHANE SL is 72 hours. There are multiple variables that will affect the full cure time, such as ambient conditions (temperature, humidity, wind, etc.), joint design (sealant width and depth), moisture content of concrete, etc.

Cleanup ... Application tools can be cleaned with toluene or xylene before curing. Afterwards, mechanical cleaning will be required.

PRECAUTIONS

Allow one-week cure at standard conditions when used in total water immersion applications. Maximum exposure level of chlorine is 5 ppm. Do not cure in presence of curing silicone sealants. Avoid contact with alcohol and other solvent cleaners during cure. POURTHANE SL is not resistant to ethanol in fully submerged or continual soaked conditions. Maximum depth of POURTHANE SL should be 1/2" (12.7 mm). Do not use caulks, sand, or incompressibles as a bottom in a joint. Do not install when rain is expected before the product develops a substantial skin. Storing at elevated temperatures will reduce shelf life.

For most recent data sheet, sustainability information, and SDS, visit www.wrmeadows.com.



LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control

over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.

© W. R. MEADOWS 2026

