


SealBoss®

1403 SLV Resin PUR



Product Data Sheet

SealBoss® 1403 Applications

- Follow-Up Injection of Water Stop Foam Injection
- Hairline Crack Injection
- Sealing Concrete Cracks & Joints
- Sealing Concrete Construction Joints
- Brick Construction
- Waste Water Tanks
- Sewers, Manholes, Utility Boxes, etc.
- Tunnels, Dams, Bridges
- SealBoss® Inject Tube System 2000

Super Low Viscosity, Flexible, Polyurethane Injection Resin

SealBoss® 1403 Advantages:

- SealBoss® Product-Pump-Packer System Solution
- Deep Penetration - 70 CPS SLV
- Full Cure in Dry & Damp Conditions
- Flexible, Moisture Insensitive, 2 Comp. Formula
- Unregulated For Transport
- This Product is for Professional Use

Product Description

SealBoss® 1403 SLV Resin is a low viscosity, two component, hydrophobic MDI polyurethane based resin on a MDI polyurethane. The product is 100% solids and solvent free. The gel time of the product can be decreased by adding a **SealBoss® 1400 Catalyst**.

This high grade injection resin is designed for application in damp and dry cracks. Unlike water activated products, SealBoss® 1403 SLV Resin does not need any moisture for the reaction. The super low viscosity of 70 cps permits for excellent penetration into fine hairline cracks. Good adhesive properties and product flexibility minimize formation of new cracks in the structure. The cured resin is inert to wet and dry cycles, it does not shrink or swell. SealBoss® 1403 SLV Resin may slightly foam in contact with moisture in a pressure free environment. Under pressure SealBoss® 1403 SLV Resin cures to a dense and flexible sealant. The product is non-corrosive and safe for use in combination with foils and joint strips. The product is an excellent finishing product for areas previously injected with expanding foam, where minor leaks or dampness may persist.

Limitations: SealBoss® 1403 SLV Resin is not designed to stop active water leaks. Larger amounts of water can dilute the product and reduce physical properties. Active leaks should be stopped first with SealBoss® WaterStopFoam, PU Injection Grouts or **SealBoss® FlexGel**. Ask your SealBoss technician for details. The product is for professional use.

Installation Guidelines

SealBoss® 1403 SLV Resin is supplied in separate containers with equal amounts of A and B component. The mixing ratio by volume is 1:1 (A:B). The material can be applied with suitable two-component or single component injection equipment.

Single component equipment users: Observe temperature and humidity of the environment, since both determine the pot life of the premixed batch. Do not mix more material than the amount that will be pumped within pot life window. Rule: High temperatures and high humidity shorten your gel time.

The use of SealBoss® 1400 Catalyst is optional: By adding 1400 Catalyst to the clear A (!) side only, gel time can be reduced from approximately 1 hour to approximately 20 minutes. Up to 5% of catalyst may be added by volume to achieve the shortest gel time.

Example of catalyst usage:

2 gal mixture (7.6 liters)

1% = approx. 2.5 fl oz or .07 liters

5% = approx. 12 fl oz or .35 liters

All equipment, pumps and hoses must be dry. Avoid moisture contact with the mixture to prevent premature reaction. If product foams while pumping, immediately shut down the machine and flush with a cleaner to avoid build up and clogging of the equipment.

Maintenance of Equipment

Tools and equipment must be cleaned immediately after use. Remove all excess product. Cured product is hard to remove. **SealBoss® R70 Pump Flush** is a solvent free, non-flammable cleaner, lubricator, pump and hose conditioner. Please refer to the product data sheet for detailed information.

Health and Safety

Protect your health! Always use safety gear in compliance with OSHA and all applicable local and job-site regulations While working with products. Handling of this product may result in spills, splashes, and airborne substances. Wear appropriate safety goggles, gloves and safety clothing at all times. During the pressure injection process a full face shield is advised for anybody within reach of product spill or blowout. Consider property in proximity of the application to prevent loss or damage. Protect jobsite from unauthorized persons. Store all materials and equipment safely and out of reach of children and animals! Observe container labels, SDS, applicable laws and regulations and all instructions before using the product and equipment. In case one of the components comes in contact with the skin, wash thoroughly with soap and water. Provide adequate ventilation in volume and pattern in working area. Further protection: emergency showers and eyewash stations. Get immediate medical attention as needed.

SealBoss®

1403 SLV Resin PUR



Product Data Sheet

Technical Properties

	Comp. A	Comp. B	1400 CAT	
Appearance	Clear	Dark Brown	Clear	
Solids	100%	100%	100%	ASTM D 2369
Density, g/ml	1.02	1.14	1.16	ASTM D 4659
Flash Point, °C / °F	156/313	180/356	165/335	ASTM D 93
Viscosity, cps	60-70	80-90	50	ASTM D 2196
Mixing Ratio by Volume	1 part	1 part	5% max	
Packaging	5 gal	5 gal	0.5 gal	
Cured Product				
Hardness, Shore D	40			
Elongation, %	>100	ASTM D 412		
Tensile Strength, psi	260	ASTM D 412		
Adhesive Strength, to Concrete, psi	>260			
Corrosiveness	Non-Corrosive			
Storage	Good storage stability for unopened containers at 15 - 30°C, 58 - 85°F in dry, sun free indoors environment 2 years shelf life.			
Appearance	Dark Brown			
Resistance to Chemicals	Resistant to Most Organic Solvents, Mild Acids, Alkali and Micro Organisms			



Limited Warranty Policy and Disclaimer for Products Supplied and/or Distributed by SealBoss Corp.: SealBoss Corp. Products are for Professional Use. All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use. SealBoss Corp. warrants supplied / distributed products to be free of manufacturing defects. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of the manufacturer which proves to be defective. There are no other warranties by SealBoss Corp. of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. SealBoss Corp. shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. SealBoss Corp. shall not be responsible for use of this product in a manner to infringe on any patent or any other intellectual property rights held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, UV damage, excessive temperature exposure, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and / or physical movement of the substrate or structural defects are also excluded from the limited warranty. SealBoss Corp. reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of or inability to use the product. Recommendations and statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. SealBoss Corp. reserves the right to change the properties of products without notice.

Revised 202501