



PRODUCT DATA SHEET

SikaQuick® EZ Patch

High performance, FAST SETTING, CEMENT BASED patch.

PRODUCT DESCRIPTION

SikaQuick® EZ Patch is a cementitious, one-component, fast setting material used for concrete surface repairs .

USES

- Used to reprofile substrates or subfloor surfaces from feather edge to a maximum 1-1/2" (38 mm) in thickness.
- Repair minor defects, holes, cracks and pre-fill static (i.e. nonmoving) joints and seams in concrete, balconies, terraces, etc.
- On grade, above grade and below grade on concrete and mortar.
- On horizontal surfaces.
- For pedestrian traffic only.

CHARACTERISTICS / ADVANTAGES

- Easy to use, one-component
- Variable water ratios to achieve different product consistency
- Interior and exterior use
- Feather edge application
- High compressive and flexural strengths
- High abrasion resistance

PRODUCT INFORMATION

Packaging	30 lb (13.6 kg) bag
Appearance / Color	Gray powder
Shelf Life	12 months from date of production if stored properly in original, unopened and undamaged, sealed packaging
Storage Conditions	Store dry at 40° - 95° F (4° - 35° C) Protect from moisture. If damp, discard material.

Product Data Sheet
SikaQuick® EZ Patch
March 2020, Version 01.03
020302040030000292

TECHNICAL INFORMATION

Compressive Strength	4 hours	1,650 psi (11.4 MPa)	(ASTM C-109) 73° F (23° C), 50% R.H.
	1 day	2,700 psi (18.6 MPa)	
	7 days	3,700 psi (25.5 MPa)	
	28 days	4,000 psi (27.6 MPa)	
Flexural Strength	28 days	1,200 psi (8.3 MPa)	(ASTM C-293) 73° F (23° C), 50% R.H.
Pull-Out Resistance	28 days	450 psi (3.1 MPa)	(ASTM C-1583) 73° F (23° C), 50% R.H.
Shrinkage	28 days	< 0.05%	(ASTM C-157 [modified per ASTM C-928]) 73° F (23° C), 50% R.H.

APPLICATION INFORMATION

Mixing Ratio		Min.	Max.
	Water content	4.5 pts (2.1 L)	6 pts (2.8 L)
	Consistency	Plastic	Fluid
Coverage	12-15 ft ² at 1/4" (1.1-1.4 m ² at 6 mm) per bag (Coverage range does not include allowance for surface profile, surface porosity or material waste.)		
Layer Thickness		Min.	Max.
	Neat	Feather edge	1-1/2" (38 mm)
	Extended	1" (25.4 mm)	3" (76 mm)
Product Temperature	65° - 75° F (18° - 24° C)		
Ambient Air Temperature	45° - 95° F (7° - 35° C)		
Substrate Temperature	45° - 95° F (7° - 35° C)		
Pot Life	~ 20 minutes		
	Temperature will affect the Application Life: <ul style="list-style-type: none"> ▪ Above 73° F (23° C) will reduce the application life and workability ▪ Below 73° F (23° C) will extend the application life and workability 		
Waiting / Recoat Times	16 - 24 hours	73° F (23° C), 50% R.H.	

Product Data Sheet
SikaQuick® EZ Patch
March 2020, Version 01.03
020302040030000292



APPLICATION INSTRUCTIONS

SURFACE PREPARATION

- Surface must be clean and sound.
- Remove all deteriorated concrete, dirt, oil, grease, and other bond inhibiting materials from the surfaces to be repaired.
- Preparation work should be done by following International Concrete Repair Institute (ICRI) standards to achieve a Concrete Surface Profile (CSP-3 minimum).
- The compressive strength of the concrete substrate should be at least 2,900 psi (20 MPa) at 28 days with a minimum Tensile Strength of 200 psi (1.4 MPa).
- To ensure optimum repair results, the effectiveness of decontamination and preparation should be assessed by a Pull-Off test.
- All cracks must be repaired before using SikaQuick® EZ Patch as a final surface.
- Substrate should be Saturated Surface Dry (SSD) with clean water prior to application. Surfaces should be dampened with no standing water remaining prior to installation.

MIXING

- As with all prebagged cement products, some settlement may have occurred during transportation and storage. Dry blending of the material is recommended.
- Pour 4.5 - 5.5 pints (2.1 - 2.6 liters) of clean, potable water [approximately 70° F (21° C)] into a suitably sized and clean mixing container, using a calibrated measuring jug, or similar, to ensure strict control of the water content (do not over-water).
- Add SikaQuick® EZ Patch to the water while slowly mixing, adding the entire contents of the bag.
- Mix with a low-speed drill (400-600 rpm) and a mud paddle to blend water and powder for approximately 2 to 3 minutes. Mix until a lump-free, uniform mix has been achieved.
- Avoid entrapment of air due to excessive mixing as this will impact performance. Do not mix more mortar than can be used within the stated application life, taking into consideration ambient and substrate temperatures.
- Refer to ACI 305R "Guide to Hot Weather Concreting" and ACI 306R "Guide to Cold Weather Concreting" for guidelines when there is a need to place this product in hot or cold temperature conditions. Thinner installations will be more sensitive to ambient and substrate temperature conditions.

EXTENSION WITH AGGREGATES

- For applications greater than 1-1/2" (38 mm) in depth, add 3/8" (10 mm) coarse aggregate.
- The aggregate must be non-reactive (reference ASTM C 1260, C 227 and C 289), clean, well graded, Saturated Surface Dry (SSD), have low absorption and high density, and comply with ASTM C 33 size number 8 per

Table 2.

- Variances in the quality of the aggregate will affect the handling and physical properties of SikaQuick® EZ Patch, resulting in different cured performance values.
- Do not use limestone aggregate.
- The addition rate is 9 lbs (4.1 kgs) of aggregate per bag. This addition rate is approximately 0.72 gallons (2.7 liters) by loose volume of aggregate.
- Do not use additional water. Maximum 5.5 pints (2.1 liters) of clean water per mix.

APPLICATION

- SikaQuick® EZ Patch must be initially scrubbed into the mechanically prepared, SSD substrate, filling all pores and voids.
- Force material against edges of repair, working toward center.
- After filling the repair area, consolidate, then screed.
- Allow product to set to desired stiffness, then finish with a wood float or a sponge float for a smooth surface, or broom for a rough finish.

CURING TREATMENT

- SikaQuick® EZ Patch must be protected against contamination and from precipitation.
- Moist curing method is not required. Allow to air cure.

LIMITATIONS

- Bonding agents (e.g. Sika® Armatec® 110 EpoCem) which cure at a slower rate than SikaQuick® EZ Patch should not be used. Follow surface preparation and "scrub coat" recommendations.
- As with all cement based materials, avoid contact with aluminum to prevent adverse chemical reaction and possible product failure. Insulate potential areas of contact by coating aluminum bars, rails, posts etc. with an appropriate epoxy such as Sikadur-32 Hi-Mod.
- SikaQuick® EZ Patch does not form a vapor barrier after cure.
- All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

Product Data Sheet
SikaQuick® EZ Patch
March 2020, Version 01.03
020302040030000292

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet
SikaQuick® EZ Patch
March 2020, Version 01.03
020302040030000292

SikaQuickEZPatch-en-US-(03-2020)-1-3.pdf

