



PRODUCT DATA SHEET

Sikagard®-185 Enviroseal

(formerly MProtect H 185)

HIGH-PERFORMANCE, BREATHABLE, WATER-BASED, PATENTED SILANE/SILOXANE BLENDED REACTIVE PENETRATING SEALER FOR LIGHTWEIGHT BLOCK

PRODUCT DESCRIPTION

Sikagard®-185 Enviroseal is a high-performance, water-based, clear, silane/siloxane reactive penetrating sealer designed to provide long-term protection for the most challenging split-faced and lightweight block as well as standard CMU.

USES

- Vertical
- Interior or exterior
- Above grade

Substrates

- Concrete block
 - Lightweight
 - Integrally colored
 - Split faced
- Porous concrete surfaces

CHARACTERISTICS / ADVANTAGES

- Water repellency extends the life of a building
- Treats lightweight block and CMU providing long-lasting protection against moisture intrusion
- VOC Compliant for EPA and most regional jurisdictions
- Excellent water bead so the substrate maintains dry appearance during rainfall
- Transparent and non-staining; does not alter surface appearance
- Breathability allows interior moisture to escape without damaging sealer
- Easy to apply

Product Data Sheet
Sikagard®-185 Enviroseal
June 2025, Version 02.02
02030321000000034

ENVIRONMENTAL INFORMATION

This product cannot be used in the South Coast Air Quality Management District (“SCAQMD”) unless the following criteria from SCAQMD Rule 1113(b)(54) are met:

- (A) Used only for reinforced concrete bridge structures for transportation projects within 5 miles of the coast or above 4,000 feet elevation or for restoration and/or preservation projects on registered historical buildings that are under the purview of a restoration architect.
- (B) Penetrate into concrete and masonry substrates and chemically react to form covalent bonds with naturally occurring minerals in the substrate.
- (C) Line the pores of concrete and masonry substrates with a hydrophobic coating, but do not form a surface film.
- (D) Improve water repellency at least 80 percent after application on a concrete or masonry substrate. This performance must be verified on standardized test specimens, in accordance with one or more of the following standards: ASTM C67, or ASTM C97/97M, or ASTM C140.
- (E) Provide a breathable waterproof barrier for concrete or masonry surfaces that does not prevent or substantially retard water vapor transmission. This performance must be verified on standardized test specimens, in accordance with ASTM E96/E96M or ASTM D6490.
- (F) Meet the performance criteria listed in the National Cooperative Highway Research Report 244 (1981), surface chloride screening applications, for products labeled and formulated for vehicular traffic.

Please review SCAQMD Rule 1113 for further information.

PRODUCT INFORMATION

Chemical Base	Sikagard®-185 Enviroseal is a water-based proprietary blend of silane and siloxane.
Packaging	5 gallon (19 L) pails 54 gallon (205 L) drums
Color	Milky white; dries clear
Appearance / Color	Appearance after application Unchanged
Shelf Life	1 year when stored properly
Storage Conditions	Store in unopened containers in a clean, dry area between 35 and 110° F (2 and 43° C). Keep from freezing.
Density	8.38 lb/gal
	Specific Gravity 1.0 kg/L
Flash Point	> 212 ° F (> 100 ° C) (ASTM D 3278)

Product Data Sheet
Sikagard®-185 Enviroseal
June 2025, Version 02.02
02030321000000034



TECHNICAL INFORMATION

Resistance to Weathering	Efflorescence Highly resistant	
Penetration Depth	1/16 – ¼ in. (1.5–6 mm) average depth depending upon substrate	
Water Tightness	99% reduction	(ASTM E 514)
Water resistance	Water Repellency > 95% reduction in water absorption	(ASTM C 140)
Light fastness of colour pigments	No yellowing	

APPLICATION INFORMATION

Coverage	Block (lightweight): 25–60 ft ² /gal (0.6–1.5 m ² /L) Porous concrete: 60–150 ft ² /gal (1.5–3.7 m ² /L) A test area is recommended to determine actual coverage rates. Coverage rates will vary greatly with the porosity of the substrate.
Drying Time	Typical drying time for Sikagard®-185 Enviroseal is 4 hours at 70° F (21° C) and 50% relative humidity. Cooler temperatures or higher relative humidity can extend the drying time. Drying time to recoat 30 min

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

- Keep material from freezing.
- Do not dilute Sikagard®-185 Enviroseal.
- Do not apply during inclement weather or when inclement weather is anticipated within 2 hours.
- To prevent damage to nearby shrubbery and landscaping, cover or protect with drop cloth.
- Variations in the texture and porosity of the substrate will affect the coverage and performance of the product.
- Protect asphalt-based products such as roofing materials or plastic products from overspray

- Sikagard®-185 Enviroseal will not inhibit water penetration through unsound or cracked surfaces or surfaces with defective flashing, caulking, or structural waterproofing.
- Make certain the most current versions of the product data sheet and SDS are being used.
- Proper application is the responsibility of the user. Field visits by Sika personnel are for the purpose of making technical recommendations only and are not for supervising or providing quality control on the jobsite.

SUBSTRATE PREPARATION

1. Surfaces should be clean, dry, and free of alkali, efflorescence, sand, surface dust or dirt, oil, grease, chemical films, and other contaminants. Concrete surfaces should be fully cured.
2. Air, material, and surface temperatures should be 40° F (4° C) or higher during application and curing. Surfaces can be slightly damp prior to application, but for best results and maximum penetration of sealer, a dry surface is recommended. Do not apply sealer when temperatures are expected to fall below 40° F (4° C) within 4 hours of the completed application.
3. Repoint any loose or disintegrated mortar and allow a minimum of 72 hours drying time before application. Install caulking and sealant before application, allowing a minimum of 6–12 hours of curing time (or until set). Contact Technical Service for recommendations.

APPLICATION

Product Data Sheet
Sikagard®-185 Enviroseal
June 2025, Version 02.02
020303210000000034



1. Test a small area of the surface (generally a 5 by 5 ft [1.5 by 1.5 m] section) before starting the general application of any clear penetrating sealer to ensure desired performance results, aesthetics, and coverage rates. Allow 2 weeks for the product to fully react before evaluating. Refer to Appendix HY-3: Test Area Application.
2. Mix material thoroughly before and during application.
3. Apply by low-pressure, non-atomizing spray.
4. Apply a mist coat of Sikagard®-185 Enviroseal immediately before application to help break surface tension and assist with maximum penetration.
5. Flood surfaces to saturation by applying from the bottom up, with a controlled 8–10" (20 cm) material rundown to ensure maximum penetration into the substrate.
6. Extremely porous substrates may require 2 coats. Application of the second coat should proceed with a wet-on-wet application. Refer to Appendix HY-1: Sealing Lightweight Block.

installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/about-us/terms-conditions-of-sale.html> or by calling 1-800-933-7452.

CLEANING OF TOOLS

Clean equipment and tools with hot soapy water. Overspray can be cleaned immediately with hot soapy water. Dried residue can be cleaned with a mild citrus-based cleaner or very hot water, then scrubbed with a soft-bristle brush.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of

Sika Corporation
 201 Polito Avenue
 Lyndhurst, NJ 07071
 Phone: +1-800-933-7452
 Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet
 Sikagard®-185 Enviroseal
 June 2025, Version 02.02
 020303210000000034

Sikagard-185Enviroseal-en-US-(06-2025)-2-2.pdf

