



MasterFormat:
03 35 00

JANUARY 2020
(Supersedes August 2018)

CURE-TREAT™ RTU

Ready-to-Use Concrete Curing Aid and Hardener

DESCRIPTION

CURE-TREAT RTU is a ready-to-use, easy-to-apply, clear, water-based concrete curing aid and hardener. Concrete surfaces treated with CURE-TREAT RTU have increased resistance to abrasion and dusting. CURE-TREAT RTU contains no solvents, waxes, or resins.

USES

CURE-TREAT RTU is ideal for improving curing, hardening, and dustproofing of exposed concrete floor slabs, sidewalks, driveways, beams, columns, etc. It can be used to provide a hard, dust-free surface on concrete floors to be painted or covered by resilient, carpeted, wood, or synthetic flooring.

FEATURES/BENEFITS

- Meets the moisture retention requirement of ASTM C309 on hard-troweled concrete.
- Ready to use/Easy to apply.
- Increases resistance to abrasion, dusting.
- Provides three different properties to concrete surfaces - curing, hardening, and dustproofing.

PACKAGING

1 Gallon (3.78 L) Units
5 Gallon (18.93 L) Pails
55 Gallon (208.20 L) Drums
275 Gallon (1040.99 L) Totes

COVERAGE

Broomed Surface: 400 ft.²/gal.
(9.82 m²/L)
Troweled Surface: 600 ft.²/gal.
(14.73 m²/L)

Coverage is approximate and may vary depending on surface finish/texture, concrete condition, climatic conditions, etc. Always apply to a test area first to determine actual coverage rate before full-scale application.

SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 40° - 90° F (4° - 32° C), optimum performance and best use is obtained within one year of date of manufacture.

SPECIFICATIONS/STANDARDS

- Complies with all current federal, state, and local maximum allowable including National EPA VOC Emission Standard for Architectural Coating, CARB, and SCAQMD.

TECHNICAL DATA

VOC Content: 0 g/L

APPLICATION

Mixing ... For optimum performance, gentle mixing or agitation is recommended.

Application Method ... Application equipment must be clean and free of any previously used materials. New Concrete: Apply CURE-TREAT RTU as soon as surface water has disappeared and the surface is dry to the touch or hard enough to walk on. Apply one even coat with a pressure hand sprayer, such as a Chapin 1949 with 0.1 GPM (0.379 LPM) nozzle, or paint roller.

Existing (Old) Concrete: Clean surface thoroughly with a trisodium phosphate solution and rinse thoroughly. Apply CURE-TREAT RTU after the surface has dried. NOTE: Keep heavy traffic off surface for 24 - 48 hours after applying CURE-TREAT RTU.

Drying Time ... Depends on weather conditions and coverage, but will generally dry in one hour.

Cleanup ... Application equipment may be cleaned easily with soap and water while still wet.

CONTINUED ON REVERSE SIDE ...

W. R. MEADOWS, INC.

P.O. Box 338 • Hampshire, IL 60140-0338
Phone: 847/214-2100 • Fax: 847/683-4544
1-800-342-5976

www.wrmeadows.com • info@wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA
FORT WORTH, TX / BENICIA, CA / POMONA, CA
GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB

PRECAUTIONS

DO NOT DILUTE. Do not apply if the temperature of the concrete is less than 40° F (4° C). KEEP FROM FREEZING. If CURE-TREAT RTU is accidentally sprayed or spilled on glass, brick, aluminum, painted surfaces, etc., flush immediately with water. DO NOT OVER APPLY. DO NOT ADD OR DILUTE WITH ANY OTHER COMPOUNDS. DO NOT MIX WITH ANY COMPOUNDS CONTAINING SOLVENT.

**LIMITED WARRANTY**

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.

© W. R. MEADOWS 2025