



PRODUCT DATA SHEET

Sika Thoroseal® Acryl 60

(formerly MEmaco A 660)

WATER-BASED ACRYLIC BONDING AND MODIFYING ADMIXTURE

PRODUCT DESCRIPTION

Sika Thoroseal® Acryl 60 is an acrylic-polymer emulsion that enhances the adhesion, physical properties, and durability of Portland cement mortars, plasters, stucco, and concrete mixes.

USES

- Interior and exterior
- Above or below grade
- Horizontal, vertical, and overhead surfaces
- Improve adhesion and durability of cement-based mixes
- As gauging liquid for Sika waterproofing and repair products, such as Sika Thoroseal®-581

Substrates

- Concrete

Industries/Sectors

- Commercial
- Residential
- Building Restoration
- Infrastructure

PRODUCT INFORMATION

Chemical Base	Sika Thoroseal® Acryl 60 is an acrylic-polymer emulsion.
Packaging	Sika Thoroseal® Acryl 60 ▪ 1-gallon (3.8 L) bottles ▪ 5-gallon (18.9 L) pails ▪ 55-gallon (208 L) drums
Shelf Life	1-gallon 5-gallon, 55-gallon drums: 12 months when properly stored.
Storage Conditions	Transport and store in unopened containers between 40° and 100 °F (4° and

Product Data Sheet
Sika Thoroseal® Acryl 60
September 2024, Version 02.01
02030100000002032

	38 °C). Protect from freezing.	
Density	8.65 lbs/gal (1.04 kg/L)	(Lab Method)
Solid content by mass	28% by Volume	(Lab Method)

TECHNICAL INFORMATION

Specific Advice	Maximum Water Dilution 1 part Sika Thoroseal® Acryl 60 to 3 parts H ₂ O	(Lab Method)
-----------------	---	--------------

Indicative performance of mortar mix

Test Data

The following properties are for sand/cement mortar samples:

Property	Results With Water	Results With 1-to-1 Sika Thoroseal® Acryl 60	Test Methods
Compressive Strength, 28 days	3,800 (26.2) psi (MPa)	4,500 (31) psi (MPa)	ASTM C 109
Tensile Strength, 28 days	225 (1.5) psi (MPa)	350 (2.4) psi (MPa)	ASTM C 190
Flexural Strength, 28 days	1,000 (6.9) psi (MPa)	1,800 (12.4) psi (MPa)	ASTM C 348
Freeze/Thaw Durability	11 at 98 cycles	102 at 300 cycles	Method A

Test results are averages obtained under laboratory conditions at 70 °F (21 °C) and 50% rh. Reasonable variations can be expected.

APPLICATION INFORMATION

Coverage	Varies according to application. See Mixing Ratio table.
----------	--

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LIMITATIONS

For Best Performance

- Do not use Sika Thoroseal® Acryl 60 when the substrate or ambient temperature is below 40 °F (4 °C) or when the temperature is expected to fall below 40 °F (4 °C) within 24 hours. High relative humidity, excessive moisture, and low temperatures will retard the curing of mixes modified with Sika Thoroseal® Acryl 60.
- Caution is required when using Sika Thoroseal® Acryl 60 in a mix that already has air entrained; consult Technical Service for its proper use.
- Do not overmix or aerate mixes.
- Use with proper ventilation.
- Do not use Sika Thoroseal® Acryl 60 as a surface-applied external bonding agent or as a primer.

- Do not subject cement-based mixes modified with Sika Thoroseal® Acryl 60 to water immersion for a minimum of 24 hours at 73 °F (23 °C).
- Not recommended for exposure to soft water or immersion where contact with water-treatment chemicals is present without a protective top coat.
- Caution should be used when a solvent-based material is being used over a base system that contains Sika Thoroseal® Acryl 60.
- For professional use only; not for sale to or use by the general public.
- Make certain the most current versions of product data sheet and SDS are being used.
- Proper application is the responsibility of the user. Field visits by Sika personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the job site.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must

Product Data Sheet
Sika Thoroseal® Acryl 60
September 2024, Version 02.01
02030100000002032

read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

1. Follow surface preparation recommendations for repair material to be used.
2. The area to be patched or coated should be in a saturated surface-dry (SSD) condition, with no standing water on surface.
3. For additional surface preparation guidelines, refer to the instructions for the Sika repair mortar or coating being used.

MIXING

1. 1 part of Sika Thoroseal® Acryl 60 is typically mixed with 3 parts of potable water. Where increased physical and chemical resistance are required, increase the Sika Thoroseal® Acryl 60 water ratio to 1:2 or 1:1 (see Mixing Ratio table below).
2. Mechanically mix at low speed to avoid trapping air. Do not overmix or mix at a high speed.

Mixing Ratios

Application	Ratios
To improve the adhesion properties of pointing mortars and to reduce cracking in cement plaster	Use 1-part Sika Thoroseal® Acryl 60 to 3-parts water
For large overlays or topping	Use 2-parts Sika Thoroseal® Acryl 60 to 1-part water
For bonding cement plaster no thicker than 1/4–3/8" (6–10 mm)	Use 1-part Sika Thoroseal® Acryl 60 to 3-parts water

Note: The above ratios are for normal conditions. Where bonding is more critical, increase the Sika Thoroseal® Acryl 60 content of the mixing liquid. A TEST PATCH IS ALWAYS RECOMMENDED.

APPLICATION

Sand/Cement Mortar

1. Thoroughly mix all cement and sand first. The sand must be clean, free of clay, and dry.
2. Makeup mixing liquid from a 1:3 or 1:2 Sika Thoroseal® Acryl 60/water mix, depending on requirements.
3. Slowly add the mixing liquid to the cement/sand mixture and mix with a slow-speed mixer for 1-2 minutes to avoid trapping air.
4. After preparing, cleaning, and pre-dampening the surface, brush-apply a scrub coat (not diluted) of the Sika Thoroseal® Acryl 60-modified cement/sand. Scrub vigorously into the surface to displace any air pockets.
5. While the scrub coat is still wet or tacky, fill the repair area with the modified cement/sand mix, being careful not to over-trowel. The trowel should be cleaned frequently, kept wet, and used with minimal pressure.

6. Maximum time for placement should not exceed 20 minutes. Higher air and surface temperatures or the use of fast-setting repair materials will decrease working and placement time.

Curing

1. When rapid drying is expected due to high temperatures, rapid air movement, or wind, it is recommended that the surface be covered with wet burlap to retain moisture.
2. For normal use, allow a 24-hour curing period.
3. For heavy-wheeled traffic, allow a 4-day curing period.

CLEANING OF TOOLS

Clean all tools and equipment immediately with water. Cured material may be removed by mechanical means.

Product Data Sheet
Sika Thoroseal® Acryl 60
September 2024, Version 02.01
02030100000002032



LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet
Sika Thoroseal® Acryl 60
September 2024, Version 02.01
02030100000002032

SikaThorosealAcryl60-en-US-(09-2024)-2-1.pdf

