



PRODUCT DATA SHEET

SikaQuick® Set-45

(formerly MEmaco T 545)

VERY RAPID-SETTING CHEMICAL ACTION MORTAR

PRODUCT DESCRIPTION

SikaQuick® Set-45 is a one-component magnesium phosphate-based mortar for ambient and substrate temperatures below 85° F (29° C).

USES

- Interior and exterior
- Horizontal and formed vertical or overhead repairs
- Applications requiring high early-strength gain
- Structural concrete repairs
- Partial and full-depth repairs
- Cold temperature repairs
- Grouting applications such as anchor bolts, rebar, dowel rods, and precast applications

Substrates

- Concrete

PRODUCT INFORMATION

Chemical Base	SikaQuick® Set-45 is a magnesium-phosphate patching and repair mortar.
Packaging	50 lb (22.6 kg) polyethylene-lined bags
Shelf Life	12 months when properly stored
Storage Conditions	Store in unopened containers in cool, clean, dry conditions

CHARACTERISTICS / ADVANTAGES

- Single component to just add water and mix
- Reaches 2,000 psi compressive strength in 1 hour to rapidly return repairs to service
- Takes rubber tire traffic in 45 minutes
- Wide temperature use ranges from below-freezing to hot weather exposures
- Very low drying shrinkage for improved bond to concrete for repair and anchoring applications
- Resistant to freeze/thaw cycles and deicing chemicals so it is usable in most environments
- Air cure only, no wet curing compounds required
- Coefficient of thermal expansion similar to Portland cement concrete for more permanent repairs
- Higher sulfate resistance than conventional mortars

Product Data Sheet
SikaQuick® Set-45
September 2024, Version 02.01
020302040030000563

TECHNICAL INFORMATION

Compressive Strength	Time	Plain Concrete at 72° F (22° C)	SikaQuick® Set-45 at 72° F (22° C)	SikaQuick® Set-45 at 36° F (2° C)	(ASTM C 109, modified)
	1 hour	-	2000psi (13.8MPa)	-	
	3 hours	-	5000psi (34.5MPa)	-	
	6 hours	-	5000psi (34.5MPa)	1200psi (8.3MPa)	
	1 day	500psi (3.5MPa)	6,000psi (41.4MPa)	5,000psi (34.5MPa)	
	3 days	1,900psi (13.1MPa)	7,000psi (48.3MPa)	7,000psi (48.3MPa)	
	28 days	4,000psi (27.6MPa)	8,500psi (58.6MPa)	8,500psi (58.6MPa)	
	<hr/>				
Modulus of Elasticity in Compression	Time	SikaQuick® Set-45			(ASTM C 469)
	7 Days	4.18 x 10 ⁶ psi (2.88 x 10 ⁴ MPa)			
	28 Days	4.55 x 10 ⁶ psi (3.14 x 10 ⁴ MPa)			
<hr/>					
Flexural Strength	1-day strength on 3 by 4 by 16" (75 by 100 by 406 mm) prisms				(ASTM C 78, modified)
	SikaQuick® Set-45: 550psi (3.8MPa)				
	SikaQuick® Set-45 with 3/8" (9 mm) pea gravel: 600psi (4.2MPa)				
	SikaQuick® Set-45 with 3/8" (9 mm) crushed angular noncalcareous hard aggregate: 650psi (4.5MPa)				
<hr/>					
Coefficient of Thermal Expansion	Hot Weather coefficients***: 7.15 x 10 ⁻⁶ /° F (12.8 x 10 ⁻⁶ /° C)				(CRD-C 39)
***Determined using 1 by 1 by 11" (25 mm by 25 mm by 279 mm) bars. The test was run with neat mixes (no aggregate).					
<hr/>					
Sulfate Resistance	SikaQuick® Set-45 length change after 52 weeks: 0.09%				(ASTM C 1012)
Type V cement mortar after 52 weeks: 0.20%					
<hr/>					
Freeze-Thaw Stability	80% RDM at 300 Cycles				(ASTM C 666, Procedure A(modified**))
**Method discontinues test when 300 cycles or an RDM of 60% is reached.					
<hr/>					
Freeze Thaw De-Icing Salt Resistance	Scaling resistance to deicing chemicals				
	5 Cycles: 0				(ASTM C 672)
	25 Cycles: 0				
50 Cycles: 1.5(slight scaling)					

APPLICATION INFORMATION

Coverage	A 50 lb (22.6 kg) bag of mixed with the required amount of water produces a volume of approximately 0.39 ft ³ (0.011 m ³); 60% extension using 1/2" (13 mm) rounded, sound aggregate produces approximately 0.58 ft ³ (0.016 m ³).	
Set Time	9-15 min at 72° F (22° C)	(Gilmore ASTM C 266, modified)
Final set time	10-20 min at 72° F (22° C)	(Gilmore ASTM C 266, modified)

Product Data Sheet
 SikaQuick® Set-45
 September 2024, Version 02.01
 020302040030000563

BUILDING TRUST



BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

APPLICATION INSTRUCTIONS

NOTES ON INSTALLATION

- Color variations are not indicators of abnormal product performance.
- SikaQuick® Set-45 will not freeze at temperatures above -20° F (-29° C) when appropriate precautions are taken.
- Do not add sand, fine aggregate, or Portland cement.
- **Do not use SikaQuick® Set-45 for repairs less than ½" (13 mm) deep. For deep repairs, use SikaQuick® Set-45 formula extended with aggregate**, regardless of the temperature. Consult your Sika representative for further instructions.
- Do not use limestone aggregate.
- Do not deviate from the recommended water content printed on the bag.
- Precondition these materials to approximately 70° F (21° C) for 24 hours before using.
- Protect repairs from direct sunlight, wind, and other conditions that could cause rapid drying of material for the first three hours.
- When mixing or placing in a closed area, provide adequate ventilation.
- Do not use it as a precision machinery grout.
- When using in contact with galvanized steel or aluminum, consult your local Sika sales representative.
- Do not mix partial bags.
- For professional use only; not for sale to or use by the general public.
- Make certain the most current versions of the product data sheet and SDS are being used.
- Proper application is the responsibility of the user. Field visits by Sika personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

SURFACE PREPARATION

1. Concrete must be structurally sound and fully cured (28 days).
2. Saw cut the perimeter of the area being repaired into a

- square with a minimum depth of ½" (13 mm).
3. Refer to current ICRI Guideline no. 310.2R for surface prep requirements to permit proper bond.
4. Any surface carbonation in the repair area will inhibit chemical bonding. Apply a pH indicator to the prepared surface to test for carbonation. If carbonation is present, abrade the surface to a depth that is not carbonated.

Product Data Sheet
SikaQuick® Set-45
September 2024, Version 02.01
020302040030000563



MIXING

1. SikaQuick® Set-45 must be mixed, placed, and finished within 10 minutes in normal temperatures (71° F [21° C]). Only mix quantities that can be placed in 10 minutes or less.
2. Do not deviate from the following sequence; it is important for reducing mixing time and producing a consistent mix. Use a minimum ½" slow-speed drill and mixing paddle or an appropriately sized forced-action mortar mixer. Do not mix by hand.
3. Pour potable water into mixer. Use a maximum of 4 pts (1.9 L) of water per 50 lb (22.6 kg) bag of SikaQuick® Set-45. Do not deviate from the recommended water content.
4. Add the powder to the water and mix for approximately 1–1½ minutes.
5. Use neat material for repairs from ½–2" (13–51 mm) in depth. **For deeper repairs, extend a 50 lb (22.6 kg) bag of SikaQuick® Set-45 by adding up to 30 lbs (13.6 kg) of properly graded, dust-free, hard, rounded aggregate or non-calcareous crushed angular aggregate, not exceeding ½" (13 mm) in accordance with ASTM C 33, #8 (Test aggregate for fizzing with 10% HCl). If the aggregate is damp, reduce the water content accordingly. Special procedures must be followed when angular aggregate is used. Contact your local Sika representative for more information.**

APPLICATION

1. Immediately place the mixture onto the properly prepared substrate. Work the material firmly into the bottom and sides of the patch to ensure good bond.
2. Level the SikaQuick® Set-45 and screed to the elevation of the existing concrete. Minimal finishing is required.

CURING TREATMENT

No curing is required but protect from rain immediately after placing. Liquid-membrane curing compounds or plastic sheeting may be used to protect the early surface from precipitation, but never wet cure.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation
 201 Polito Avenue
 Lyndhurst, NJ 07071
 Phone: +1-800-933-7452
 Fax: +1-201-933-6225
usa.sika.com



Product Data Sheet
 SikaQuick® Set-45
 September 2024, Version 02.01
 020302040030000563

