



## PRODUCT DATA SHEET

# Sikadur®-32 Hi-Mod LPL

High-modulus, high-strength, extended pot life, epoxy bonding/grouting adhesive

### PRODUCT DESCRIPTION

Sikadur®-32 Hi-Mod LPL is a multi-purpose, 2-component, 100% solids, moisture-tolerant, structural epoxy adhesive. Sikadur®-32 Hi-Mod LPL offers a long pot life and contact time even at 100 °F (38 °C). Sikadur®-32 Hi-Mod LPL conforms to the current ASTM C-881, Types I and II, Grade-2, Class-C and AASHTO M-235 specifications.

### USES

Sikadur®-32 Hi-Mod LPL may only be used by experienced professionals.

- Hot weather concrete placements requiring a bonding adhesive.
- Bond fresh, plastic concrete to hardened concrete and steel.
- Grout horizontal cracks in structural concrete and wood by gravity feed.
- Machinery and baseplate grout.
- Structural adhesive for concrete, masonry, metal, wood, etc.

### CHARACTERISTICS / ADVANTAGES

- Extended pot life and contact time at elevated temperatures.
- High-strength bonding/grouting adhesive.
- Tolerant of moisture before, during, and after cure.
- Excellent adhesion to most structural materials.
- Convenient easy-to-mix ratio A:B = 1:1 by volume.
- Easy-to-use for bonding/grouting applications.

### PRODUCT INFORMATION

<b>Packaging</b>	1 (3.8 L) and 4 gal. (15.1 L) units
<b>Color</b>	Dark gray
<b>Shelf Life</b>	24 months in original, unopened containers
<b>Storage Conditions</b>	Store dry at 40–95 °F (4–35 °C). Condition material to 65–75 °F (18–24 °C) before using
<b>Viscosity</b>	Approximately 2,800 cps.

Product Data Sheet  
Sikadur®-32 Hi-Mod LPL  
October 2018, Version 01.01  
020204030010000130

**TECHNICAL INFORMATION**

<b>Compressive Strength</b>		<b>40 °F* (4 °C)</b>	<b>73 °F* (23 °C)</b>	(ASTM D-695) 50 % R.H.
	1 day	-	-	
	3 day	-	10,700 psi (73.8 MPa)	
	7 day	2,500 psi (17.2 MPa)	11,000 psi (75.9 MPa)	
	14 day	8,300 psi (57.2 MPa)	12,000 psi (82.3 MPa)	
	28 day	10,000 psi (68.9 MPa)	13,000 psi (89.7 MPa)	
* Material cured and tested at the temperatures indicated.				
<b>Modulus of Elasticity in Compression</b>	2.6 x 10 <sup>5</sup> psi (1,794 MPa) (28 days)			(ASTM D-695) 73 °F (23 °C) 50 % R.H.
<b>Flexural Strength</b>	9,100 psi (62.8 MPa) (14 days)			(ASTM D-790) 73 °F (23 °C) 50 % R.H.
<b>Modulus of Elasticity in Flexure</b>	7.3 X 10 <sup>5</sup> psi (5,037 MPa) (14 days)			(ASTM D-790) 73 °F (23 °C) 50 % R.H.
<b>Tensile Strength</b>	5,800 psi (40.0 MPa) (14 days)			(ASTM D-638) 73 °F (23 °C) 50 % R.H.
<b>Elongation at Break</b>	5 % (14 days)			(ASTM D-638) 73 °F (23 °C) 50 % R.H.
<b>Shear Strength</b>	6,400 psi (44.1 MPa) (14 days)			(ASTM D-732) 73 °F (23 °C) 50 % R.H.
<b>Slant Shear Strength</b>	Plastic concrete to hardened concrete	2,200 psi (15.2 MPa)	14 day (moist cure)	(ASTM C-882) 73 °F (23 °C) 50 % R.H.
	Plastic concrete to steel	2,200 psi (15.2 MPa)	14 day (moist cure)	
	Hardened concrete to hardened concrete	3,100 psi (21.3 MPa)	2 day (dry cure)	
	Hardened concrete to hardened concrete	2,900 psi (20 MPa)	14 day (moist cure)	
	Hardened concrete to hardened concrete			
<b>Heat Deflection Temperature</b>	108 °F (42 °C) (14 days at (fiber stress loading = 264 psi {1.8 MPa}))			(ASTM D-648)
<b>Water Absorption</b>	0.15 % (7 days, 4 hours)			(ASTM D-570)

**APPLICATION INFORMATION**

<b>Mixing Ratio</b>	Component 'A' : Component 'B' = 1:1 by volume
---------------------	---

Product Data Sheet  
Sikadur®-32 Hi-Mod LPL  
October 2018, Version 01.01  
020204030010000130

**BUILDING TRUST**



**Pot Life** Approximately 90 minutes at 73 °F (23 °C). (8 fl. oz., 237 ml volume)  
 Approximately 60 minutes at 100 °F (38 °C). (8 fl. oz., 237 ml volume)

Contact Time	Substrate Temperature 40 °F (4 °C)	Substrate Temperature 73 °F (23 °C)	Substrate Temperature 90 °F (32 °C)
	Material Temperature 73 °F (23 °C)	10–14 h	6–7 h
Material Temperature 100 °F (38 °C)	6–8 h	5–6 h	1.5–2 h

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

Surface must be clean and sound. It may be dry or damp, but free of standing water. Remove dust, laitance, grease, curing compounds, impregnations, waxes and any other contaminants.

**Preparation Work:** Concrete - Should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by blast cleaning or equivalent mechanical means.

**Steel** - Should be cleaned and prepared thoroughly by blast cleaning or other equivalent mechanical means.

### MIXING

Pre-mix each component. Proportion equal parts by volume of Component 'A' and Component 'B' into clean pail. Mix thoroughly for 3 minutes with Sika paddle on low-speed (400–600 rpm) drill until blend is a uniform color. Mix only that quantity that can be applied within its pot life.

### APPLICATION METHOD / TOOLS

**To bond fresh concrete to hardened concrete** - Apply by brush, roller, broom, or spray. Place fresh concrete while Sikadur®-32 Hi-Mod LPL is still tacky. If coating becomes glossy and loses tackiness, remove any surface contaminants then recoat with additional Sikadur®-32 Hi-Mod LPL and proceed.

**To grout base plates** - Add 1 1/2 parts of oven-dried aggregate to 1 part of mixed Sikadur®-32 Hi-Mod LPL by volume. Place grout under baseplate. Avoid contact with the underside of the plate. A 1/4 to 3/8 in. (6–10 mm) space should remain between the top of the grout and the bottom of the plate. Maximum thickness of grout per lift is 1.5 in. (38 mm) If multiple lifts are needed, allow preceding layer to cool to touch before applying additional layer. The remaining 1/4 to 3/8 in. (6–10 mm) space should be filled with neat Sikadur®-32 Hi-Mod LPL. Pour a sufficient quantity of neat epoxy to allow the level to rise slightly higher than the underside of the

bearing plate.

**To gravity feed cracks** - Pour neat material into vee-notched crack. Continue placement until completely filled. Seal underside of slab prior to filling if cracks reflect through.

### LIMITATIONS

- Minimum substrate and ambient temperature 40 °F (4 °C)
- For spray applications, consult Technical Service
- Use only oven-dry aggregate
- Material is a vapor barrier after cure
- For applications on exterior, on-grade substrates, consult Technical Service
- Not an aesthetic product. Color may alter due to variations in lighting and/or UV exposure

### BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

### OTHER RESTRICTIONS

See Legal Disclaimer.

### ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

### LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED

Product Data Sheet  
 Sikadur®-32 Hi-Mod LPL  
 October 2018, Version 01.01  
 020204030010000130



- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

**Sika Corporation**  
 201 Polito Avenue  
 Lyndhurst, NJ 07071  
 Phone: +1-800-933-7452  
 Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)

**Sika Mexicana S.A. de C.V.**  
 Carretera Libre Celaya Km. 8.5  
 Fracc. Industrial Balvanera  
 Corregidora, Queretaro  
 C.P. 76920  
 Phone: 52 442 2385800  
 Fax: 52 442 2250537



**Product Data Sheet**  
 Sikadur®-32 Hi-Mod LPL  
 October 2018, Version 01.01  
 020204030010000130

Sikadur-32Hi-ModLPL-en-US-(10-2018)-1-1.pdf

