



MasterFormat:

03 01 00

03 64 23

JULY 2025

(Supersedes February 2025)

REZI-WELD™ LV

Low Viscosity Injection Epoxy

DESCRIPTION

REZI-WELD LV low viscosity injection epoxy is a moisture insensitive, very low viscosity, high modulus, high strength, structural injection resin. REZI-WELD LV resists most chemicals and features a unique, innovative unitized packaging concept. It combines two pre-measured components into an easy-to-handle single unit along with a handy wood-mixing paddle (1 gal. unit only). The unitized packaging eliminates mishandling and mismatching of the components on the jobsite.

USES

REZI-WELD LV is designed for gravity feeding or pressure injecting using two-component metering systems, hand-held bulk guns, or pressure pots. It is suitable for injecting fine, non-moving structural cracks for long-term repairs.

When mixed with sand or aggregates, REZI-WELD LV makes an economical, easy-to-use epoxy mortar for patching or repairing defects in concrete substrates, securing machinery base plates to concrete floors, interior non-skid toppings, and structural bonding applications.

REZI-WELD LV may also be used as a primer before application of DECK-O-SEAL® joint sealant products. Refer to INSTALLATION GUIDELINES: DECK-O-SEAL LINE WITH REZI-WELD LV PRIMER for full details.

FEATURES/BENEFITS

- Ideal for pressure injection and gravity feeding.
- Advantageous as a low viscosity, epoxy adhesive binder.
- Bonds cured concrete to fresh or hardened concrete.
- Combines with aggregate to form an interior non-skid topping.
- Resists many industrial chemicals.
- Features low viscosity, high modulus, high strength, self-leveling characteristics.
- Furnished in unitized packaging.
- Can be extended with sand to make an epoxy mortar.

PACKAGING

1 Quart (.95 Liter) Units
1 Gallon (3.79 Liter) Units

COVERAGE

One gallon (3.8 L) neat covers approximately 85 - 100 ft.² (2.09 - 2.66 m²/L) depending on the surface porosity and end use application. One gallon (3.8 L) mixed 1:1 with dry aggregate yields approximately 350 in.³ (5735 cm³) of grout. One quart neat covers 21.25 - 27.5 ft.² (0.52 - 0.675 m²/L). Coverage dependent on surface porosity and end use application.

SHELF LIFE

Two years from date of manufacture when stored indoors on pallets in a dry, cool area. Do not store product outside.

SPECIFICATIONS/STANDARDS

- ASTM C881 Type I, II, IV and V, Grade 1, Class B & C
- AASHTO M 235 Type I, II, IV and V, Grade 1, Class B & C
- USDA accepted
- Various department of transportation approvals

TECHNICAL DATA

Property 7 Day Cure @ 77° F (25° C)	Typical Data	Test Method
Tensile Strength, psi	7000 (48.3 MPa)	ASTM D638
Elongation, %	1.6	ASTM D 638
Hardness, Shore D	85	ASTM D2240
Flexural Strength, psi	8000 (55.2 MPa)	ASTM D790
Flexural Modulus, psi	520,000 (3585 MPa)	ASTM D790
Compressive Yield Strength, psi	12,000 (82.7 MPa)	ASTM D695
Compressive Modulus, psi	260,000 (1800 MPa)	ASTM D695
Bond Strength, psi (2 days)	2500 (17.25 MPa)	ASTM C882
Bond Strength, psi (14 days)	3200 (22.08 MPa)	ASTM C882
Absorption, % (24 hours)	0.13%	ASTM D570
Linear Coefficient of Shrinkage	0.004	ASTM D2566

Component Properties	Resin	Hardener
Mix Ratio (PBV=Part by Vol.)	2 PBV	1 PBV
Appearance	Clear	Amber
Wt./gal, lb./gal. (Kg/L)	9.6 (1.15 Kg/L)	8.2 (.98 Kg/L)

Pot Life [1 Qt. Unit (0.95 L @ 77° F (25° C))]: 30 min.

Mixed Color: Medium Amber

Mixed Viscosity: 2000 Cps

CONTINUED ON REVERSE SIDE ...

W. R. MEADOWS, INC.

P.O. Box 338 • Hampshire, IL 60140-0338
Phone: 847/214-2100 • Fax: 847/683-4544
1-800-342-5976

www.wrmeadows.com • info@wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA
FORT WORTH, TX / BENICIA, CA / POMONA, CA
GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB

All technical data is typical information, but may vary due to test methods, conditions and operators.

APPLICATION

Surface Preparation ... All surfaces to be bonded must be free of standing water and completely clean of dirt, rust, curing compounds, grease, oil, paint, waxes, and other materials that would prevent an optimal bond. Concrete should be prepared by mechanical abrading or grit blasting to a sound and profiled surface. Vacuum or blow dust away with oil-free compressed air. Mechanically abrade metal base plates to a bright metal finish. Exposed steel surfaces should be sandblasted and vacuumed clean; if not possible, degrease the surface and use sandpaper or a wire brush to reveal continuous, bright metal.

Mixing... Condition all components to 60° - 85° F (16° - 29° C) for 24 hours prior to use. Use the double-boiler method or store material in a warm room prior to application. Premix each component. Mechanically mix at slow speed (600 - 900 rpm) using a drill and Jiffy® Blade or drum mixer for three minutes or until completely mixed while scraping the sides to ensure complete blending of components. Avoid air entrapment. Mix only the amount of epoxy that can be applied within the product's pot life. Pot life will decrease as the ambient temperature and/or mass size increases.

Crack Injecting ... Epoxy can be gravity fed into horizontal cracks that are small (1/4" [6.35 mm] maximum width) and have limited depth. For large injection projects, self-proportioning, mixing, and pressure injection equipment is recommended. For small injection projects REZI-WELD LV STATE may be suitable.

Interior, Non-Skid Topping ... Apply at a rate of 100 ft.²/gal. (2.66 m²/L). Then apply layer of sand or grit over epoxy and allow to set. Blow excess sand away. NOTE: REZI-WELD LV IS NOT TO BE USED AS A FINISHED FLOOR COVERING OR PROTECTIVE TREATMENT. Follow standard epoxy flooring system requirements, including water vapor transmission rates.

Aggregates for Epoxy-Resin Mortars ...

Combine clean, dry aggregates with freshly mixed epoxy in a ratio of 1 part epoxy to 1 to 4 parts, by volume, of graded aggregates (not to exceed six parts sand). Patch thickness should not exceed 4" (101.6 mm) per lift.

Cleanup... Clean tools and equipment immediately with toluene or xylene. Clean equipment away from all ignition sources and avoid breathing vapors or allowing epoxy-containing solvent to contact skin. Should this material come in contact with the skin, wash thoroughly with soap and water, not solvent.

PRECAUTIONS

DO NOT DILUTE. Mix complete units only. Not recommended for use when the concrete and air temperature is below 40° F (4° C) or will drop below 40° F (4° C) within 24 hours. Do not use to seal cracks under hydrostatic pressure. Do not warm epoxy over direct heat. REZI-WELD LV should not be used as an exterior coating, as it is not color stable to ultraviolet light (sun). REZI-WELD LV should not be applied to existing concrete until it is at least 14 days old and has reached 80% of its original design strength.

HEALTH AND SAFETY

This epoxy is corrosive. Personal protective equipment is necessary. Unused epoxy will generate excessive heat, especially in large quantities. Unused epoxy should be mixed with dry sand in the container to help lower heat. Refer to Safety Data Sheet for complete health and safety information.

For most current data sheet, sustainability information, and SDS, visit www.wrmeadows.com.



LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control

over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.

© W. R. MEADOWS 2025