


MIRAFI 140NC



MIRAFI® 140NC is a needlepunched nonwoven geotextile composed of polypropylene fibers, which are formed into a stable network such that the fibers retain their relative position. MIRAFI 140NC is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

TenCate Geosynthetics Americas (A Solmax Company) is accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](#)).

MIRAFI 140NC meets Build America, Buy America Act, Pub. L. No. 117-58, div. G §§ 70901-52.

MECHANICAL PROPERTIES	TEST METHOD	UNIT	MINIMUM AVERAGE ROLL VALUE	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs (N)	100 (445)	100 (445)
Grab Tensile Elongation	ASTM D4632	%	50	50
Trapezoid Tear Strength	ASTM D4533	lbs (N)	45 (200)	45 (200)
CBR Puncture Strength	ASTM D6241	lbs (N)	250 (1113)	
MAXIMUM OPENING SIZE				
Apparent Opening Size (AOS)	ASTM D4751	U.S. Sieve (mm)	70 (0.212)	
MINIMUM ROLL VALUE				
Permittivity	ASTM D4491	sec ⁻¹	2.0	
Flow Rate	ASTM D4491	gal/min/ft ² (l/min/m ²)	140 (5704)	
MINIMUM TEST VALUE				
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	70	
PHYSICAL PROPERTIES		UNIT	ROLL SIZE	
Roll Dimensions (width x length)		ft (m)	12.5 x 360 (3.8 x 110)	15 x 360 (4.57 x 110)
Roll Area		yd ² (m ²)	500 (418)	600 (502)
Roll Weight		lbs (kg)	145 (66)	170 (77)

365 South Holland Drive Pendergrass, GA 30567

Tel +1 706 693 2226 www.tencategeo.us



Solmax is not a design or engineering professional and has not performed any such design services to determine if Solmax's goods comply with any project plans or specifications, or with the application or use of Solmax's goods to any particular system, project, purpose, installation, or specification.
FGS000388 ETQR74

