



Product Description

ULTRABOND® 2 is a two-component, 1:1 mix ratio, structural epoxy system that offers exceptional strength in anchoring and doweling applications and can be used in temperatures from 40 °F to 110 °F (4 °C to 43 °C). It has been tested in accordance with ASTM E488 and ASTM E1512 for its capability to resist static, dynamic, seismic and wind loads in uncracked concrete for both threaded rod and rebar.

General Uses & Applications

- Anchoring threaded rod into uncracked concrete
- Short and long term tensile anchoring, including wind, seismic and shear forces in accordance with allowable stress design (ASD)
- Grouting dowel bars and tie bars for full depth concrete pavement repairs

Advantages & Features

- Extended working time
- Moisture insensitive allowing installation and curing in damp environments
- In-service temperature range between 35 °F (2 °C) and 180 °F (82 °C)
- Withstands freeze-thaw conditions
- Little or no odor
- High modulus

Availability: Adhesives Technology Corp. (ATC) products are available through select distributors providing you with all your construction needs. Please contact ATC for a distributor near you or visit our website at www.atcepoxy.com to search by zip code.

Color & Ratio: Part A (Resin): White, Part B (Hardener): Black, Mixed: Concrete Gray, Mix Ratio: 1:1 by volume.

Storage & Shelf Life: 28 months when stored in unopened containers in dry conditions. Store between 40 °F (4 °C) and 95 °F (35 °C).

Installation & Estimation: See Manufacturer's Printed Installation Instructions (MPII) available within this Technical Data Sheet (TDS). Due to occasional updates and revisions, always verify that you are using the most current version of the MPII. In order to achieve maximum results, proper installation is imperative. An estimating guide for product usage can be found at www.atcepoxy.com.

Clean Up: Always wear appropriate protective equipment such as safety glasses and gloves. Clean uncured materials from tools and equipment with mild solvent. Cured material can only be removed mechanically.

Limitations & Warnings:

- Do not thin with solvents, as this may affect cure
- For anchoring applications, concrete should be a minimum of 21 days old prior to anchor installation
- Not recommended for any application where there may be a sustained tensile load, including overhead applications
- Performance characteristics, such as seismic and long term load resistance, were tested in accordance with ASTM E488-96 (2003) & E1512-01 (2015) provisions and not that of ACI 355.4, and are therefore not applicable in the concrete tension zone - always consult with a design professional prior to use to ensure product applicability

Safety: Please refer to the Safety Data Sheet (SDS) for ULTRABOND 2 published on our website or call ATC for more information at 1-800-892-1880.

Specification: Anchoring adhesive shall be a two component, 1:1 ratio, high viscosity, solvent free epoxy system supplied in pre-measured containers. Epoxy must have a compressive yield strength of 10,688 psi (73.7 MPa) at 75 °F after a 7 day cure. Shelf life must be a minimum of 28 months. Adhesive shall be ULTRABOND 2 from Adhesives Technology Corp., Pompano Beach, Florida. Anchors shall be installed per the Manufacturer's Printed Installation Instructions (MPII) for ULTRABOND 2 anchoring epoxy.

STANDARDS & APPROVALS

Multiple DOT Listings

(See ATC website for current list of Department of Transportation approvals throughout the United States)

Revision 8.0

ULTRABOND²

Extended Working Time Epoxy

Anchoring

ORDERING INFORMATION



A22-2N



TM22HD



TA22HD-A



T3438C



HBHT



HBEXT



HB100

TABLE 1: ULTRABOND 2 Adhesive, Dispensing Tools and Mixing Nozzles

Package Size	21.2 oz. (627 ml) Cartridge
Part #	A22-2N
Manual Dispensing Tool	TM22HD
Pneumatic Dispensing Tool	TA22HD-A
Case Qty.	12
Pallet Qty.	576
Pallet Weight (lbs.)	1,578
Recommended Mixing Nozzle	T3438C ¹

1. For projects with hole diameters greater than 3/4 in. the T3412CT can be used on A22-2N cartridge.

TABLE 2: Wire Brushes, Handles and Adapters

Part #	Threaded Rod Diameter in.	Rebar Diameter	Nominal Brush Diameter in.	Minimum Brush Diameter in.	Qty.
HB038	3/8	#3	5/8	0.563	1
HB012	1/2	#4	3/4	0.675	1
HB058	5/8	#5	1	0.900	1
HB034	3/4	#6	1 1/4	1.125	1
HB078	7/8	#7	1 1/2	1.350	1
HB100	1	#8	1 5/8	1.463	1
HB125	1 1/4	---	1 3/4	1.575	1
HBHT	Steel brush 12" usable extension with T-Handle (manual)				1
HBEXT	Steel brush 12" usable extension with SDS + drill adaptor				1

MATERIAL SPECIFICATION

TABLE 3: ULTRABOND 2 performance to ASTM C881-14¹

Property	Cure Time	ASTM Standard	Units	Sample Conditioning Temperature
				Class C 75 °F (24) °C
Gel Time - 60 Gram Mass	----	C881	min	12
Compressive Yield Strength	7 day	D695	psi (MPa)	10,688 (73.7)
Tensile Strength		D638	psi (MPa)	545 (3.8)
Tensile Elongation			%	6.0
Consistency or Viscosity	----	C881	----	Non-sag

1. Results based on testing conducted on a representative lot(s) of product. Average results will vary according to the tolerances of the given property.

TABLE 4: ULTRABOND 2 CURE SCHEDULE^{1,2,3}

Base Material Temperature	Working Time	Full Cure Time
40 (4)	60 min	72 hr
75 (24)	28 min	48 hr
110 (43)	12 min	24 hr

1. Working and full cure times are approximate, may be linearly interpolated between listed temperatures and are based on cartridge/nozzle system performance.

2. Application Temperature: Substrate and ambient air temperature should be from 40 °F - 110 °F (4 °C - 43 °C).

3. When ambient or base material temperature falls below 70 °F (21 °C), condition the adhesive to 70 °F - 75 °F (21 °C - 24 °C) prior to use.

Revision 8.0


ULTRABOND²

Extended Working Time Epoxy


Anchoring

INSTALLATION INSTRUCTIONS (MPII)


Drilling and Cleaning



Using a rotary hammer drill, and a bit which conforms to ANSI B212.15 and is the appropriate size for the anchor diameter to be installed, drill the hole to the specified embedment depth. **CAUTION:** Always wear appropriate personal protection equipment (PPE) for eyes, ears & skin and avoid inhalation of dust during the drilling and cleaning process. Refer to the Safety Data Sheet (SDS) for details prior to proceeding.



NOTE: Remove any standing water from hole prior to beginning the cleaning process. If removal of standing water is not possible, please contact ATC for application specific installation instructions. Using oil free compressed air with a minimum pressure of 80 psi (5.5 bar), insert the air wand to the bottom of the drilled hole and blow out the debris with an up/down motion for a minimum of 4 seconds/cycles (4X).



Select the correct wire brush size for the drilled hole diameter (see Table 2), making sure that the brush is long enough to reach the bottom of the drilled hole. Reaching the bottom of the hole, brush in an up/down and twisting motion for 4 cycles (4X). **CAUTION:** The brush should contact the walls of the hole. If it does not, the brush is either too worn or small and should be replaced with a new brush of the correct diameter.




Blow the hole out once more to remove brush debris using oil free compressed air with a minimum pressure of 80 psi (5.5 bar). Insert the air wand to the bottom of the drilled hole and blow out the debris with an up/down motion for a minimum of 4 seconds/cycles (4X). Visually inspect the hole to confirm it is clean.

NOTE: If installation will be delayed for any reason, cover cleaned holes to prevent contamination.

Cartridge Preparation



CAUTION: Check the expiration date on the cartridge to ensure it is not expired. **Do not use expired product!** Remove the protective cap from the adhesive cartridge and insert the cartridge into the recommended dispensing tool. Before attaching mixing nozzle, balance the cartridge by dispensing a small amount of material until both components are flowing evenly. For a cleaner environment, hand mix the two components and let cure prior to disposal in accordance with local regulations.




Only after the cartridge has been balanced, screw on the proper ATC mixing nozzle to the cartridge (see Table 1). Do not modify mixing nozzle and confirm that internal mixing element is in place prior to dispensing adhesive. Take note of the air and base material temperatures and review the working/full cure time chart (see Table 4) prior to starting the injection process.




Dispense the initial amount of material from the mixing nozzle onto a disposable surface until the product is a uniform gray color with no streaks, as adhesive must be properly mixed in order to perform as published. Dispose of the initial amount of adhesive according to local regulations prior to injection into the drill hole. **CAUTION:** When changing cartridges, never re-use nozzles. A new nozzle should be used with each new cartridge and steps 5-7 should be repeated accordingly.


Installation and Curing (Vertical Down and Horizontal)



NOTE: The engineering drawings must be followed. For any applications not covered by this document, or if there are any installation questions, please contact Adhesives Technology Corp. Insert the mixing nozzle to the bottom of the hole and fill from the bottom to the top approximately two-thirds full, being careful not to withdraw the nozzle too quickly as this may trap air in the adhesive. **NOTE:** When using a pneumatic dispensing tool, ensure that pressure is set at 90 psi (6.2 bar) maximum.



Prior to inserting the threaded rod or rebar into the hole, make sure it is clean and free of oil and dirt and that the necessary embedment depth is marked on the anchor element. Insert the anchor element into the hole while turning 1 - 2 rotations prior to the anchor reaching the bottom of the hole. Excess adhesive should be visible on all sides of the fully installed anchor. For horizontal installations, wedges should be used to center and support the anchor while the adhesive is curing. **CAUTION:** Use extra care with deep embedment or high temperature installations to ensure that the working time has not elapsed prior to the anchor being fully installed.



Do not disturb, torque or apply any load to the installed anchor until the specified full cure time has passed. The amount of time needed to reach full cure is base material temperature and moisture dependent - refer to Table 4 for appropriate full cure time.

Revision 8.0

TECHNICAL DATA



TABLE 5: ULTRABOND 2 IN-SERVICE CHART¹

Base Material Temperature	Allowable Load Capacity Reduction Factor
°F (°C)	
35 (2)	1.00
70 (21)	1.00
110 (43)	1.00
135 (57)	0.79
150 (66)	0.79
180 (82)	0.65

1. Reduction factors may be linearly interpolated between listed temperatures.

TABLE 6: ULTRABOND 2 ultimate and allowable TENSION loads for THREADED ROD in normal-weight concrete^{1,2}

Threaded Rod Diameter in.	Nominal Drill Bit Diameter in.	Embedment Depth in. (mm)	Tension Load Based on Bond Strength/Concrete Capacity				Allowable Tension Load Based on Steel Strength ³		
			$f'_c \geq 2,000$ psi (20.7 MPa) ⁴		$f'_c \geq 4,000$ psi (27.6 MPa) ⁴		ASTM F1554 Grade 36 lbs. (kN)	ASTM A193 Grade B7 lbs. (kN)	ASTM F593 304/316 SS lbs. (kN)
			Ultimate lbs. (kN)	Allowable lbs. (kN)	Ultimate lbs. (kN)	Allowable lbs. (kN)			
3/8	7/16	3 1/2 (89)	8,637 (38.4)	2,159 (9.6)	8,637 (38.4)	2,159 (9.6)	2,114 (9.4)	4,556 (20.3)	3,645 (16.2)
1/2	9/16	4 1/2 (114)	17,076 (76.0)	4,269 (19.0)	17,953 (79.9)	4,488 (20.0)	3,758 (16.7)	8,099 (36.0)	6,480 (28.8)
5/8	3/4	5 5/8 (143)	23,865 (106.2)	5,966 (26.5)	28,356 (126.1)	7,089 (31.5)	5,872 (26.1)	12,655 (56.3)	10,124 (45.0)
3/4	7/8	6 3/4 (171)	31,371 (139.5)	7,843 (34.9)	38,709 (172.2)	9,677 (43.0)	8,456 (37.6)	18,224 (81.1)	12,392 (55.1)
7/8	1	7 7/8 (200)	39,532 (175.8)	9,883 (44.0)	48,410 (215.3)	12,103 (53.8)	11,509 (51.2)	24,804 (110.3)	16,867 (75.0)
1	1 1/8	9 (229)	48,299 (214.8)	12,075 (53.7)	60,648 (269.8)	15,162 (67.4)	15,033 (66.9)	32,398 (144.1)	22,030 (98.0)
1 1/4	1 3/8	11.25 (286)	67,500 (300.3)	16,875 (75.1)	90,626 (403.1)	22,657 (100.8)	23,488 (104.5)	50,621 (225.2)	34,423 (153.1)

1. Allowable bond strength/concrete capacity was calculated using a safety factor of 4.0.
2. The lower value of either the allowable bond strength/concrete capacity or steel strength should be used as the allowable tension value for design.
3. Allowable steel strengths calculated in accordance with AISC Manual of Steel Construction: $Tensile = 0.33 \cdot F_u \cdot A_{nom}$.
4. Linear interpolation may be used for intermediate concrete compressive strengths.

Revision 8.0

ULTRABOND²

Extended Working Time Epoxy

Anchoring

TECHNICAL DATA



TABLE 7: ULTRABOND 2 ultimate and allowable SHEAR loads for THREADED ROD in normal-weight concrete^{1,2}

Threaded Rod Diameter in.	Nominal Drill Bit Diameter in.	Embedment Depth in. (mm)	Shear Load Based on Bond Strength/Concrete Capacity		Allowable Shear Load Based on Steel Strength ³		
			$f_c \geq 2,000$ psi (20.7 MPa) ⁴		ASTM F1554 Grade 36 lbs. (kN)	ASTM A193 Grade B7 lbs. (kN)	ASTM F593 304/316 SS lbs. (kN)
			Ultimate lbs. (kN)	Allowable lbs. (kN)			
1/2	9/16	4 1/2 (114)	13,090 (58.2)	3,273 (14.6)	1,936 (8.6)	4,172 (18.6)	3,338 (14.8)
5/8	3/4	5 5/8 (143)	20,892 (92.9)	5,223 (23.2)	3,025 (13.5)	6,519 (29.0)	5,216 (23.2)
3/4	7/8	6 3/4 (171)	31,721 (141.1)	7,930 (35.3)	4,356 (19.4)	9,388 (41.8)	6,384 (28.4)
7/8	1	7 7/8 (200)	36,577 (162.7)	9,144 (40.7)	5,929 (26.4)	12,778 (56.8)	8,689 (38.7)
1	1 1/8	9 (229)	53,165 (236.5)	13,291 (59.1)	7,744 (34.4)	16,690 (74.2)	11,349 (50.5)
1 1/4	1 3/8	11 1/4 (286)	83,052 (369.4)	20,763 (92.4)	12,100 (53.8)	26,078 (116.0)	17,733 (78.9)

1. Allowable bond strength/concrete capacity was calculated using a safety factor of 4.0.
2. The lower value of either the allowable bond strength/concrete capacity or steel strength should be used as the allowable shear value for design.
3. Allowable steel strengths calculated in accordance with AISC Manual of Steel Construction: $Shear = 0.17 \cdot F_u \cdot A_{nom}$.

Revision 8.0