



# CONCRETE-TOP SUPREME

## SINGLE COMPONENT CEMENTITIOUS TOPPING & REPAIR MORTAR

**EUCLID CHEMICAL**

### DESCRIPTION

CONCRETE-TOP SUPREME is a latex and microsilica modified, cementitious mortar designed for use as a concrete repair mortar at thicknesses of 3/8" to 2" (9.5 mm to 50 mm). This product is a single-component formula which incorporates a powder latex technology, providing protection from corrosion and excellent durability under freeze-thaw cycles as well as reducing ingress by water and de-icing salts.

### PRIMARY APPLICATIONS

- Parking decks
- Warehouse floors
- Shoulder repairs
- Walkways
- Pavements
- Light industrial floors
- Ramps

### FEATURES/BENEFITS

- Provides a strong, wear resistant overlay
- Contains an integral corrosion inhibitor
- Excellent bond to properly prepared sound concrete
- Compatible with galvanic anodes
- Suitable for both interior and exterior use
- Formulated for easy placement

### TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

**Compressive Strength** ASTM C 109, 2" (50 mm) cubes

Age	Strength
1 day.....	4,000 psi (27.6 MPa)
7 days.....	7,000 psi (48.3 MPa)
28 days.....	9,000 psi (62.1 MPa)
56 days.....	9,500 psi (65.5 MPa)

**Flexural Strength** ASTM C 348

7 days.....	1,200 psi (8.3 MPa)
28 days.....	1,250 psi (8.6 MPa)

**Linear Shrinkage** ASTM C 157 50% RH @ 23°C (73°F)  
(specimens were removed from molds @ 24 hours)

14 days.....	-0.10%
56 days.....	-0.13%

**Chloride Permeability** ASTM C 1202

28 days.....	1,200 coulombs
--------------	----------------

**Freeze/Thaw Resistance** ASTM C 666 Procedure A

300 Cycles.....	92% relative dynamic modulus
-----------------	------------------------------

**Working Time** ..... approx. 30 min**Initial Set** ..... approx. 1 hour**Final Set** ..... approx. 3 hours**Unit Weight**.....approx. 140 lb/ft<sup>3</sup> (2243 kg/m<sup>3</sup>)

CONCRETE-TOP SUPREME is a free-flowing powder as packaged. After mixing and placing, the color may initially appear darker than the surrounding concrete, but will lighten substantially as it cures.

### PACKAGING/YIELD

CONCRETE-TOP SUPREME is packaged in 50 lb (22.7 kg) moisture resistant bags. **Yield:** is 0.40 ft<sup>3</sup>/bag (0.011 m<sup>3</sup>) when mixed with 2.5 qt (2.4 L) of water. Typical water requirement is 2.0 to 3.0 qt (1.9 to 2.8 L)/bag. A unit of material may be extended with 15 lb (6.8 kg) of 3/8" (9.5 mm) pea gravel. This will yield 0.47 ft<sup>3</sup> (0.013 m<sup>3</sup>) and may be used for overlay placements that exceed 2" (50 mm) in depth.

### SHELF LIFE

2 years in original, unopened package

### SPECIFICATIONS/COMPLIANCES

Canadian Food Inspection Agency, MTQ, MTO

## DIRECTIONS FOR USE

**Surface Preparation:** Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Mechanically abrade the surface to achieve a surface profile equal to CSP 5-7 in accordance with ICRI Guideline 310.2. Properly clean profiled area.

**Priming & Bonding (Horizontal Toppings):** For the best adhesion to concrete, use EUCOFLOOR EPOXY PRIMER seeded with sand as the bonding coat. Refer to the EUCOFLOOR EPOXY PRIMER technical data sheet for full instructions. Alternatively, application of EUROWELD 2.0 to a dry substrate or a scrub coat of CONCRETE-TOP SUPREME to the saturated surface dry (SSD) concrete surface may be used for bonding. The topping material must be placed on the scrub coat before the scrub coat dries out.

**Mixing:** A single bag of CONCRETE-TOP SUPREME may be mixed with a drill and “jiffy” mixer. Use a paddle type mortar mixer for large jobs. All material should be in the proper temperature range of 45°F (7°C) to 90°F (32°C). Add the appropriate amount of water, 2 to 3 qt (1.9 to 2.8 L)/bag, then slowly add the dry product. Mix for 3 to 5 minutes.

**Placement:** For patching, spread with a trowel, come-a-long, or square tipped shovel to a thickness that matches the surrounding concrete. When used as an overlay, use screed strips along with vibratory screeding to level.

**Finishing:** Finish the repair material to the desired texture. This product is designed for finishing with a float or broom texture. A steel trowel finish may be applied but timing of the final trowel is critical. For a hard, flat troweled surface, delay finishing until the product is near final set to reduce the risk of blistering during troweling. Do not add additional water to the surface during the finishing operation. If additional liquid is required, use EUCOBAR evaporation retarder. **NOTE:** Always re-establish joints when using this product as an overlay.

**Curing and Sealing:** Proper curing procedures are important to ensure the durability and quality of the repair. To reduce surface cracking, cure the floor with a high solids curing compound, such as SUPER AQUA-CURE VOX or SUPER DIAMOND CLEAR VOX. Note: Do not use a solvent based curing compound on this product. If a curing compound is not desired, cover with quality plastic sheeting for a minimum of three days.

## CLEAN-UP

Clean tools and equipment with water before the material hardens.

## PRECAUTIONS/LIMITATIONS

- Do not allow repairs to freeze until the material has reached a minimum 1,000 psi (7 MPa) compressive strength.
- Use only potable water for mixing.
- Do not use material at temperatures below 45°F (7°C).
- When necessary, follow the recommendations in ACI 305R “Guide to Hot Weather Concreting” or ACI 306R “Guide to Cold Weather Concreting”.
- Always mix full units.
- Do not use a solvent based curing compound on this product.
- Do not use DURALPREP A.C. as a bonding agent for toppings and overlays done with CONCRETE-TOP SUPREME.
- Store product in a dry place.
- In all cases, consult the Safety Data Sheet before use.

Rev. 07.20

**WARRANTY:** The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.