# **EUCOLASTIC 1NS**



# SINGLE-COMPONENT, NON-SAG POLYURETHANE HYBRID SEALANT

### **DESCRIPTION**

**EUCOLASTIC 1NS** is a single-component, non-sag, low-modulus, moisture-cured, polyurethane hybrid joint sealant. EUCOLASTIC 1NS is formulated with a unique silane-terminated polyurethane polymer, that provides unequaled performance against stand-alone polyurethane sealants. EUCOLASTIC 1NS is an extremely durable sealant in dynamic joints, offering persistent adhesion once fully cured.

## **PRIMARY APPLICATIONS**

- · Concrete control & expansion joints
- · Precast concrete panels
- EIFS
- · Window & door perimeters

- Masonry
- Interior and exterior applications
- Above and below grade

## FEATURES/BENEFITS

- Skins rapidly and is tack-free in 3 to 4 hours @ 75°F (24°C)
- Service temperature range: -40°F to 185°F (-40°C to 85°C)
- · Remains adhesively and cohesively bonded during temperature cyclic movement
- Extraordinary movement capability of +/- 35%
- · Can be painted

## **TECHNICAL INFORMATION**

#### **Typical Engineering Data**

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

PROPERTY	RESULTS
Rheology ASTM C639	Grade NS (Non-Sag), < 0.1875" (4.8 mm)
Extrusion Rate ASTM C1183	57.9 ml/min.
Hardness, Shore A ASTM C661	25
Movement Capability ASTM C719	+/- 35%
Skin Time	1 hr.
Tack Free Time ASTM C679	5-6 hr.
Adhesion-in-Peel ASTM C794	Concrete 18-22 Pli (31.5-38.5 N/cm) No adhesion loss
Stain & Color Change ASTM C510	No stain/No color change
Effects of Accelerated Aging ASTM C793	No Cracking or Chalking

**Appearance:** Eucolastic 1NS is a single-component sealant available in the following colors: Black, Bronze, Gray, Limestone, Stone, and White.

# PACKAGING/YIELD

EUCOLASTIC 1NS is available in cases of 10.1 oz. (300 ml) cartridges (30 cartridges per case). One cartridge yields 18 in³ (294 cm³), and will cover 24 linear feet (7.3 m) in a 1/4" x 1/4" (6 mm x 6 mm) joint.

#### SHELF LIFE

18 months in original, unpunctured cartridge

# SPECIFICATIONS/COMPLIANCES

- ASTM C920, Type S, Grade NS, Class 35, Use NT, M, A, and O
- U.S. Federal Specification TT-S-00230C Class A, Type II
- ASTM C1248
- CAN/CGSB 19.13-M87

## **DIRECTIONS FOR USE**

**Joint Dimensions:** Joint width should be 4 times the expected joint movement, but not less than 1/4" (6 mm). Width to depth ratios should be equal for joints that are 1/4" (6 mm) to 1/2" (13 mm) in width. If joint width is 1/2" (13 mm) to 1" (25 mm), the depth of EUCOLASTIC 1NS should be 1/2 the width, with 1/2" (13 mm) being the maximum allowable depth of EUCOLASTIC 1NS. Use backer rod or bond breaker tape to limit the depth of application and to prevent three-sided adhesion. **Applications of EUCOLASTIC 1NS that are deeper than what is recommended can cause bubbling or incomplete curing of the material.** 

**Surface Preparation**: New concrete must be minimum of 28 days old. The joint must be clean and sound. All oil, dirt, debris, paint and any other foreign material must be removed. The final step in cleaning should be the complete removal of all residue by solvent wiping the joint. Substrates must be dry at time of application. Wet or damp joints will cause bubbling of the sealant.

**Priming:** EUCOLASTIC 1NS typically bonds to common construction materials without a primer. However, due to the variance in surface textures of some non-porous materials (metal, glass, certain stones, etc.), a field adhesion test is recommended on these materials to verify adhesion or the need for a primer. The field adhesion test for joint sealants is described in ASTM C1193. EUCOLASTIC PRIMER is required to prime the joint facing when the sealant will be in service under water after application and curing. See Eucolastic Primer technical data sheet for use instructions.

**Mixing:** EUCOLASTIC 1NS is a single-component sealant and requires no pre-blending. It should be used directly from the cartridge.

**Placement:** Ensure that all the necessary preparation work is completed. Place backer rod or bond breaker tape into the joints and make sure they are secured in place. Using standard caulking guns, dispense the sealant directly from the cartridge into the joint. Once the joint is full, tool the sealant using a rounded spatula to create a concave surface. The concave shape will help the sealant stretch properly as the joint moves. Tooling will also put a little pressure on the sealant to aid with initial adhesion.

**Curing:** EUCOLASTIC 1NS requires no special curing. The moisture in the air and substrate will cure the sealant. A skin forms on the surface in about 1 hour at 75°F (24°C) and 50% relative humidity. It will be tack-free in 3-4 hours. EUCOLASTIC 1NS cures at rate of about 1/16" (1.6 mm) per day. The cure time will increase or decrease as temperatures and humidity levels fluctuate.

#### CLEAN-UP

Tools, equipment and general clean-up can be done with EUCO SOLVENT or xylene before the material dries. Removal of dried Eucolastic 1NS can only be done by mechanical means.

## PRECAUTIONS/LIMITATIONS

- The surface temperature of the substrate must be at least 40°F (4°C) and rising, but below 150°F (66°C), at the time of application.
- For best results, store sealant at room temperature prior to application.
- · Contact surfaces must be clean and dry.
- Do not use underneath a polyurethane deck coating unless the sealant has fully cured.
- In all cases, consult the Safety Data Sheet before use.