

Distributed By:

**UNITIS**

CONTRACTOR SUPPLIES

San Diego: 1-858-332-2133  
El Cajon: 1-619-270-7100  
Buena Park: 1-714-522-0055  
Corona: 1-951-231-9700  
www.unitisonline.com

BUILDING TRUST



## PRODUCT DATA SHEET

# SikaCem<sup>®</sup>-103

Machine-applied, silica fume enhanced, cementitious mortar

### PRODUCT DESCRIPTION

SikaCem<sup>®</sup>-103 is a ready-to-use, non-accelerated, cementitious, silica fume enhanced mortar with a dust control agent. SikaCem<sup>®</sup>-103 is formulated for machine applications using dry or wet process spray equipment.

### USES

- SikaCem<sup>®</sup>-103 is particularly suitable for structural repairs in large area applications; for structures such as bridges, viaducts, retaining walls, parking structures, tunnels, galleries, industrial and residential buildings, piers, off-shore platforms, etc.
- Use on grade, above, and below grade on concrete and mortar.
- Use on vertical, overhead and horizontal surfaces.

### CHARACTERISTICS / ADVANTAGES

- One-component, ready to use mortar
- Excellent adhesion to currently prepared, sound substrates
- High compressive and flexural strength, rapid strength and development
- High density
- Formulated to minimize dust formation
- Low in rebound, extremely economical in use
- Low water cement ratio, very low shrinkage
- Can be troweled and screed after application

### PRODUCT INFORMATION

<b>Packaging</b>	55 lb (25 kg) bag
<b>Appearance / Color</b>	Gray powder
<b>Shelf Life</b>	12 months from date of production if stored properly in original, unopened and undamaged sealed packaging
<b>Storage Conditions</b>	Store dry at 40–95 °F (4–35 °C) Condition material to 65–75 °F before using Protect from moisture. If damp, discard material
<b>Density</b>	137 lb/ft <sup>3</sup> (2.2 kg/l) (ASTM C-138)

Product Data Sheet  
SikaCem<sup>®</sup>-103  
August 2018, Version 01.01  
020302030100000014

## TECHNICAL INFORMATION

<b>Compressive Strength</b>	<b>2 days</b>	6,000 psi (41.4 MPa)	(ASTM C-109)
	<b>7 days</b>	7,000 psi (48.3 MPa)	73 °F (23 °C)
	<b>28 days</b>	8,000 psi (55.2 MPa)	100 % R.H.
* Cubes casted by spray application			
<b>Modulus of Elasticity in Compression</b>	<b>28 days</b>	5.8x10 <sup>6</sup> psi (40 GPa)	(ASTM C-496)
<b>Flexural Strength</b>	<b>7 days</b>	1,000 psi (6.9 MPa)	(ASTM C-298)
	<b>28 days</b>	1,400 psi (9.7 MPa)	73 °F (23 °C) 100 % R.H.
<b>Tensile Strength</b>	<b>7 days</b>	600 psi (4.1 MPa)	(ASTM C-496)
	<b>28 days</b>	750 psi (5.2 MPa)	73 °F (23 °C) 100 % R.H.
<b>Pull-Out Resistance</b>	<b>28 days</b>	290-580 psi (2.0-4.0 MPa)	(ASTM C-1583)
* Mortar scrubbed into substrate at 73 °F (23 °C) and 50 % R.H.			
<b>Freeze-Thaw Stability</b>	<b>300 cycles</b>	95 %	(ASTM C-666)
<b>Rapid Chloride Permeability</b>	<b>28 days</b>	> 750 C	(ASTM C-1202 AASHTO T-277)

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	5-6 pts (2.4-2.8 L) per bag		
<b>Coverage</b>	0.48 ft <sup>3</sup> (0.01 m <sup>3</sup> ) per bag (Yield in service will vary according to amount of water utilized in the shotcreting process)		
<b>Layer Thickness</b>		<b>Min.</b>	<b>Max.</b>
	Large areas	1/3" (8 mm)	2" (50 mm)
	Local application	1/4" (6 mm)	6-10" (150-250 mm)
<b>Ambient Air Temperature</b>	> 40 °F (4 °C)		
<b>Substrate Temperature</b>	> 40 °F (4 °C)		

# APPLICATION INSTRUCTIONS

## SURFACE PREPARATION

- Surface must be clean and sound. Remove all deteriorated concrete, dirt, oil, grease, and other bond-inhibiting materials from the area to be repaired.
- Steel reinforcement must be clean and free from any rust.
- Be sure repair area is not less than 1/3" (8 mm) in depth.
- Preparation work should be done by high pressure water blast, scabblor or other appropriate mechanical means to obtain an exposed aggregate surface profile (CSP-6).
- To ensure optimum repair results, the effectiveness of decontamination and preparation should be assessed by a pull-off test.
- Substrate should be Saturated Surface Dry (SSD) with clean water prior to application. No standing water should remain during application.

## PRIMING

- **Reinforcing steel:** Steel reinforcement should be thoroughly prepared by mechanical cleaning to remove all traces of rust. Where corrosion has occurred due to the presence of chlorides, the steel should be high pressure washed with clean water after mechanical cleaning. For priming of reinforcing steel use Sika® Armatec® 110 EpoCem (consult PDS).
- **Concrete Substrate:** When applying on critical substrates, the use of Sika® Armatec® 110 EpoCem as a bonding agent is advised.

## APPLICATION

- Apply SikaCem®-103 mortar by spraying or trowelling for repairing vertical or overhead surfaces.
- Shoot perpendicular (90°) to the surface. This minimizes rebound, creates the smoothest pattern (reduces 'bumps') and properly encases the rebars.
- The velocity of the material is sufficient if, at a distance of 18 to 24" (457 to 609 mm), the material pattern flattens out on contact with the surface and the rebars are encased.
- After applying the material, allow it to stiffen for about 10 minutes before removing bumpy areas with a trowel.
- Before applying the next layer, allow the material to reach initial set. This will take anywhere from 2-4 hours, depending on mix consistency, mix and ambient temperature, wind conditions and humidity.
- Begin and finish a given patch on the same day.

## Dry Process

- SikaCem®-103 is applied by conventional dry spray shotcrete equipment.
- Generally, do not use equipment with high rotor capacity.
- Apply SikaCem®-103 in accordance with ACI 506-R85, "Guide to Shotcrete". Important factors to observe during shotcreting are nozzle distance (2–6 ft.), angle to substrate (90 °), and consistency of mortar.
- Immediately after application and before set, mortar consistency should be plastic, like a firm jelly.

## Wet Process

- Conventional wet-process spray equipment such as the Mayco ST-45 or C-30HD machine should be used.
- Set up wet-process equipment; then add the water (5-6 pts per bag) directly into mixer.
- Start the mixer in motion and add the SikaCem®-103 mortar while continuing to mix.
- Mix for 3 minutes to uniform consistency.

## Natural gun finish

- If a gun-finish is too rough, special finishes may be applied.
- Approximately 5–10 min. after initial set, excess material should be sliced off with a sharp-edged cutting screed. The surface may then be finished to your requirements:
  - Broomed for a rough texture
  - Wood-floated for a granular texture
  - Steel-trowelled for a smooth finish

## CURING TREATMENT

- As per ACI recommendations for Portland cement concrete, curing is required.
- Moist cure with wet burlap and polyethylene, a fine mist of water or a water based\* compatible curing compound.
- Curing compounds adversely affect the adhesion of following lifts of mortar, leveling mortar or protective coatings.
- Moist curing should commence immediately after finishing.
- Protect freshly applied mortar from direct sunlight, wind, rain and frost.

\* Pretesting of curing compound is recommended.

## LIMITATIONS

- Do not use solvent-based curing compounds.
- As with all cement based materials, avoid contact with aluminum to prevent adverse chemical reaction and possible product failure. Insulate potential areas of contact by coating aluminum bars, rails, posts etc. with an appropriate epoxy such as Sikadur® Hi-Mod 32.
- Not a vapor barrier.

## BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## OTHER RESTRICTIONS

See Legal Disclaimer.

## ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

### DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

0 g/l

(EPA method 24)

## LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at [usa.sika.com](http://usa.sika.com) or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

#### Sika Corporation

201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: +1-800-933-7452  
Fax: +1-201-933-6225  
[usa.sika.com](http://usa.sika.com)

#### Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537



#### Product Data Sheet

SikaCem®-103  
August 2018, Version 01.01  
020302030100000014

Distributed By:



San Diego: 1-858-332-2133  
El Cajon: 1-619-270-7100  
Buena Park: 1-714-522-0055  
Corona: 1-951-231-9700  
[www.unitisonline.com](http://www.unitisonline.com)

SikaCem-103-en-US-(08-2018)-1-1.pdf

