



NO. 368-B

Distributed By:



San Diego: 1-858-332-2133  
El Cajon: 1-619-270-7100  
Buena Park: 1-714-522-0055  
Corona: 1-951-231-9700  
www.unitisonline.com

W. R. MEADOWS®



MasterFormat: 03 39 23

SEPTEMBER 2019  
(Supersedes April 2017)

## VOCOMP®-25

Water-Based, Acrylic Concrete Curing and Sealing Compound

### DESCRIPTION

VOCOMP-25 is a ready-to-use concrete curing and sealing compound formulated of special acrylic polymers in a true water-based carrier. VOCOMP-25 resists yellowing from ultraviolet exposure and provides a durable, long-lasting finish that offers improved resistance to chemicals, petroleum, and abrasives.

VOCOMP-25 appears milky white in the container and, when first applied, leaves a bluish cast on the concrete for easy visual coverage. VOCOMP-25 dries clear to provide a transparent sheen finish. This sheen can be controlled by the number of coats applied.

### USES

VOCOMP-25 may be used wherever a medium-to-high sheen is desired to bring out the natural beauty of concrete without discoloring, checking, or peeling. It may be applied to simultaneously cure, seal, and dustproof new, old, interior, exterior, horizontal, and vertical concrete surfaces. VOCOMP-25 is ideal for curing, sealing, and dustproofing driveways, sidewalks, patios, swimming pool areas, and commercial floors. Horizontal surfaces protected with VOCOMP-25 offer excellent wearing qualities for foot and vehicular traffic. If, after prolonged usage, traffic patterns appear, the surface can be washed clean and recoated to restore the original beauty. Good concrete and good concreting practices should be followed, as VOCOMP-25 is not a cure-all for improperly mixed or placed concrete.

### FEATURES/BENEFITS

- Permeable film allows moisture in cured concrete to evaporate.
- Provides a ready-to-use, non-yellowing, water-based compound that cures and seals concrete in one quick and easy application.
- 25% solids formulation.
- Minimizes hair-checking, premature cracking, dusting, and spalling.
- Dries quickly on new concrete to provide a clear, tough, easy-to-clean sheen finish.

- Applicable for use on new, old, interior, exterior, horizontal, and vertical concrete surfaces.
- Tough, durable finish offers improved resistance to chemicals, petroleum, and abrasives.
- VOC-compliant.

### PACKAGING

- 1 Gallon (3.79 Liter) Units (4 per Case)
- 5 Gallon (18.93 Liter) Pails
- 55 Gallon (208.20 Liter) Drums

### COVERAGE

- Broomed Surface: Approximately 300 ft.<sup>2</sup>/gal. (7.35 m<sup>2</sup>/L).
- Troweled Surface: Approximately 500 ft.<sup>2</sup>/gal. (12.26 m<sup>2</sup>/L).

Coverage is approximate and may vary depending on surface finish/texture, concrete condition, climatic conditions, etc. Always apply to a test area first to determine actual coverage rate before full-scale application.

### SHELF LIFE

When stored indoors in original, unopened containers at temperatures between 40° - 90° F (4° - 32° C), optimum performance and best use is obtained within one year of date of manufacture.

### SPECIFICATIONS

- AASHTO M 148, Type 1, Class A & B
- ASTM C309 Type 1, Class A & B
- ASTM C1315, Type I, Class A
- Complies with U.S. EPA, LADCO, and OTC Phase I VOC regulations.
- Dried film is USDA accepted.

### TECHNICAL DATA

VOC Content: 123 g/L

*CONTINUED ON REVERSE SIDE ...*

### W. R. MEADOWS, INC.

P.O. Box 338 • HAMPSHIRE, IL 60140-0338  
Phone: 847/214-2100 • Fax: 847/683-4544  
1-800-342-5976  
www.wrmeadows.com

HAMPSHIRE, IL / CARTERSVILLE, GA / YORK, PA  
FORT WORTH, TX / BENICIA, CA / POMONA, CA  
GOODYEAR, AZ / MILTON, ON / SHERWOOD PARK, AB

## APPLICATION

**Surface Preparation ...** Old Concrete: Surface preparation is extremely important. Concrete must always be clean and dry, with all stains, oil, grease, dust, and dirt removed prior to application. If not, they will be amplified by the transparent sheen finish. CAUTION: If a liquid compound other than VOCOMP-20, VOCOMP-25, or VOCOMP-30 has been used, do not apply VOCOMP-25 until all traces of the compound have been completely removed and the surface is clean and dry.

New Concrete: Apply VOCOMP-25 when the surface water has disappeared and the concrete surface will not be marred by walking workers.

**Mixing ...** For optimum performance, gentle mixing or agitation is recommended. CAUTION: DO NOT MIX EXCESSIVELY.

**Application Method ...** A typical industrial sprayer, such as a Chapin 1949, and a nozzle that produces a flow of 0.1 GPM (0.379 LPM) is recommended.

Spray on in a fine, fog pattern without spurts and dribbles to form a thin, continuous film. AVOID PUDDLING in low areas. If puddles occur, brush or roll them out. For added protection and a greater sheen on new or old concrete, two coats of VOCOMP-25 may be applied at right angles. Additional coats of VOCOMP-25 may be applied after the first coat has thoroughly dried. VOCOMP-25 can also be applied using a lint-free roller or lambs wool applicator. Care should be taken to maintain a wet-edge during application to prevent roller marks in dried film.

**Drying Time ...** VOCOMP-25 dries quickly. Drying times may be extended, depending on application rate, temperature, humidity, and project conditions. Restrict foot traffic for at least four hours. Twelve hours is preferable.

**Cleanup ...** While VOCOMP-25 is still wet, equipment may be cleaned with soap and water. Once dried, the material may be removed with a solvent, such as xylene or toluene.



## LIMITED WARRANTY

W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty. Copy furnished upon request.

## Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.

## PRECAUTIONS

**KEEP FROM FREEZING.** Do not dilute. Do not apply VOCOMP-25 when air, material, and surface temperatures are expected to fall below 40° F (4° C) within four hours of completed application. DO NOT MIX WATER-BASED COMPOUNDS WITH ANY COMPOUND CONTAINING SOLVENT.

VOCOMP-25 may be applied to colored concrete, but mottling may occur. Do not use on dense or non-porous surfaces, i.e., brick, stone, hard-troweled concrete, etc.

For any alternate adhesion specifications or requirements besides ASTM C1315, Section 8.8, secure the approval of the manufacturer of any paint, coating, carpet, adhesive, resilient flooring, floor topping, etc. (any type/composition of subsequent floor treatment) that will be applied over VOCOMP-25. Obtain this approval before applying the product over concrete previously applied with VOCOMP-25.

Caution should be taken when applying to dense surfaces. Over-application or buildup of the film may result in the film being scratched by pallets or objects being dragged across it. In areas intended for heavy forklift traffic, consider MED-CURE™ and/or the LIQUI-HARD® products from W. R. MEADOWS

## HEALTH AND SAFETY

Direct contact may result in mild irritation. Inhalation may cause irritation of the respiratory tract. Refer to Safety Data Sheet for complete health and safety information.

## LEED INFORMATION

May help contribute to LEED credits:

- MRc9: Construction and Demolition Waste Management

**For most current data sheet, further LEED information, and SDS, visit [www.wrmeadows.com](http://www.wrmeadows.com).**